

# $\kappa$ alumina ( $\text{Al}_2\text{O}_3$ ) Structure:


A2B3\_oP40\_33\_4a\_6a-001

This structure originally had the label A2B3\_oP40\_33\_4a\_6a. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043

<https://aflow.org/p/SGA3>

[https://aflow.org/p/A2B3\\_oP40\\_33\\_4a\\_6a-001](https://aflow.org/p/A2B3_oP40_33_4a_6a-001)



Prototype	$\text{Al}_2\text{O}_3$
AFLOW prototype label	A2B3_oP40_33_4a_6a-001
Mineral name	$\kappa$ alumina
ICSD	84375
Pearson symbol	oP40
Space group number	33
Space group symbol	$Pna2_1$
AFLOW prototype command	<pre>aflow --proto=A2B3_oP40_33_4a_6a-001 --params=a, b/a, c/a, x1, y1, z1, x2, y2, z2, x3, y3, z3, x4, y4, z4, x5, y5, z5, x6, y6, z6, x7, y7, z7, x8, y8, z8, x9, y9, z9, x10, y10, z10</pre>


## Other compounds with this structure

$(\text{Fe}_2\text{O}_3)_{1-x} \cdot (\text{Al}_2\text{O}_3)_x$ ,  $(\text{Fe}_2\text{O}_3)_{1-x} \cdot (\text{Ga}_2\text{O}_3)_x$

- Alumina comes in a variety of forms. In the Encyclopedia we have:

- Corundum, or  $\alpha$ -alumina ( $D5_1$ ) is the mineral usual found in nature.
  - $\beta$ -alumina ( $D5_6$ )
  - We describe  $\gamma$ -alumina ( $D5_7$ ) using  $\text{Fe}_2\text{O}_3$  as the prototype.
  - $\delta$ -alumina is a tetragonal distortion of the spinel structure. It is found in nature as deltalumite.
  - $\kappa\text{-Al}_2\text{O}_3$  (this structure)
- (Hermann, 1937) assigned this the *Strukturbericht* designation  $D5_6$ , calling it  $\beta$ -corundum, and subtitled the section “with small  $\text{Na}_2\text{O}$  impurities.” (Yoshioka, 2007) use this is an approximation to the true crystal structure of  $\epsilon\text{-Ga}_2\text{O}_3$ .

### Simple Orthorhombic primitive vectors



### Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	$a x_1 \hat{\mathbf{x}} + b y_1 \hat{\mathbf{y}} + c z_1 \hat{\mathbf{z}}$	(4a)	Al I
$\mathbf{B}_2$	$-x_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$-a x_1 \hat{\mathbf{x}} - b y_1 \hat{\mathbf{y}} + c (z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al I
$\mathbf{B}_3$	$(x_1 + \frac{1}{2}) \mathbf{a}_1 - (y_1 - \frac{1}{2}) \mathbf{a}_2 + z_1 \mathbf{a}_3$	$a (x_1 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_1 - \frac{1}{2}) \hat{\mathbf{y}} + c z_1 \hat{\mathbf{z}}$	(4a)	Al I
$\mathbf{B}_4$	$-(x_1 - \frac{1}{2}) \mathbf{a}_1 + (y_1 + \frac{1}{2}) \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$-a (x_1 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_1 + \frac{1}{2}) \hat{\mathbf{y}} + c (z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al I
$\mathbf{B}_5$	$x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$a x_2 \hat{\mathbf{x}} + b y_2 \hat{\mathbf{y}} + c z_2 \hat{\mathbf{z}}$	(4a)	Al II
$\mathbf{B}_6$	$-x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$-a x_2 \hat{\mathbf{x}} - b y_2 \hat{\mathbf{y}} + c (z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al II
$\mathbf{B}_7$	$(x_2 + \frac{1}{2}) \mathbf{a}_1 - (y_2 - \frac{1}{2}) \mathbf{a}_2 + z_2 \mathbf{a}_3$	$a (x_2 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_2 - \frac{1}{2}) \hat{\mathbf{y}} + c z_2 \hat{\mathbf{z}}$	(4a)	Al II
$\mathbf{B}_8$	$-(x_2 - \frac{1}{2}) \mathbf{a}_1 + (y_2 + \frac{1}{2}) \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$-a (x_2 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_2 + \frac{1}{2}) \hat{\mathbf{y}} + c (z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al II
$\mathbf{B}_9$	$x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$a x_3 \hat{\mathbf{x}} + b y_3 \hat{\mathbf{y}} + c z_3 \hat{\mathbf{z}}$	(4a)	Al III
$\mathbf{B}_{10}$	$-x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$-a x_3 \hat{\mathbf{x}} - b y_3 \hat{\mathbf{y}} + c (z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al III
$\mathbf{B}_{11}$	$(x_3 + \frac{1}{2}) \mathbf{a}_1 - (y_3 - \frac{1}{2}) \mathbf{a}_2 + z_3 \mathbf{a}_3$	$a (x_3 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_3 - \frac{1}{2}) \hat{\mathbf{y}} + c z_3 \hat{\mathbf{z}}$	(4a)	Al III
$\mathbf{B}_{12}$	$-(x_3 - \frac{1}{2}) \mathbf{a}_1 + (y_3 + \frac{1}{2}) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$-a (x_3 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_3 + \frac{1}{2}) \hat{\mathbf{y}} + c (z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al III
$\mathbf{B}_{13}$	$x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$a x_4 \hat{\mathbf{x}} + b y_4 \hat{\mathbf{y}} + c z_4 \hat{\mathbf{z}}$	(4a)	Al IV
$\mathbf{B}_{14}$	$-x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$-a x_4 \hat{\mathbf{x}} - b y_4 \hat{\mathbf{y}} + c (z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al IV
$\mathbf{B}_{15}$	$(x_4 + \frac{1}{2}) \mathbf{a}_1 - (y_4 - \frac{1}{2}) \mathbf{a}_2 + z_4 \mathbf{a}_3$	$a (x_4 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_4 - \frac{1}{2}) \hat{\mathbf{y}} + c z_4 \hat{\mathbf{z}}$	(4a)	Al IV
$\mathbf{B}_{16}$	$-(x_4 - \frac{1}{2}) \mathbf{a}_1 + (y_4 + \frac{1}{2}) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$-a (x_4 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_4 + \frac{1}{2}) \hat{\mathbf{y}} + c (z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Al IV
$\mathbf{B}_{17}$	$x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$a x_5 \hat{\mathbf{x}} + b y_5 \hat{\mathbf{y}} + c z_5 \hat{\mathbf{z}}$	(4a)	O I
$\mathbf{B}_{18}$	$-x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$-a x_5 \hat{\mathbf{x}} - b y_5 \hat{\mathbf{y}} + c (z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	O I
$\mathbf{B}_{19}$	$(x_5 + \frac{1}{2}) \mathbf{a}_1 - (y_5 - \frac{1}{2}) \mathbf{a}_2 + z_5 \mathbf{a}_3$	$a (x_5 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_5 - \frac{1}{2}) \hat{\mathbf{y}} + c z_5 \hat{\mathbf{z}}$	(4a)	O I

$\mathbf{B}_{20}$	$= -\left(x_5 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_5 + \frac{1}{2}\right) \mathbf{a}_2 + \left(z_5 + \frac{1}{2}\right) \mathbf{a}_3$	$= -a \left(x_5 - \frac{1}{2}\right) \hat{\mathbf{x}} + b \left(y_5 + \frac{1}{2}\right) \hat{\mathbf{y}} + c \left(z_5 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O I
$\mathbf{B}_{21}$	$= x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	$= ax_6 \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(4a)	O II
$\mathbf{B}_{22}$	$= -x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 + \left(z_6 + \frac{1}{2}\right) \mathbf{a}_3$	$= -ax_6 \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c \left(z_6 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O II
$\mathbf{B}_{23}$	$= \left(x_6 + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_6 - \frac{1}{2}\right) \mathbf{a}_2 + z_6 \mathbf{a}_3$	$= a \left(x_6 + \frac{1}{2}\right) \hat{\mathbf{x}} - b \left(y_6 - \frac{1}{2}\right) \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(4a)	O II
$\mathbf{B}_{24}$	$= -\left(x_6 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_6 + \frac{1}{2}\right) \mathbf{a}_2 + \left(z_6 + \frac{1}{2}\right) \mathbf{a}_3$	$= -a \left(x_6 - \frac{1}{2}\right) \hat{\mathbf{x}} + b \left(y_6 + \frac{1}{2}\right) \hat{\mathbf{y}} + c \left(z_6 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O II
$\mathbf{B}_{25}$	$= x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	$= ax_7 \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \hat{\mathbf{z}}$	(4a)	O III
$\mathbf{B}_{26}$	$= -x_7 \mathbf{a}_1 - y_7 \mathbf{a}_2 + \left(z_7 + \frac{1}{2}\right) \mathbf{a}_3$	$= -ax_7 \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c \left(z_7 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O III
$\mathbf{B}_{27}$	$= \left(x_7 + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_7 - \frac{1}{2}\right) \mathbf{a}_2 + z_7 \mathbf{a}_3$	$= a \left(x_7 + \frac{1}{2}\right) \hat{\mathbf{x}} - b \left(y_7 - \frac{1}{2}\right) \hat{\mathbf{y}} + cz_7 \hat{\mathbf{z}}$	(4a)	O III
$\mathbf{B}_{28}$	$= -\left(x_7 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_7 + \frac{1}{2}\right) \mathbf{a}_2 + \left(z_7 + \frac{1}{2}\right) \mathbf{a}_3$	$= -a \left(x_7 - \frac{1}{2}\right) \hat{\mathbf{x}} + b \left(y_7 + \frac{1}{2}\right) \hat{\mathbf{y}} + c \left(z_7 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O III
$\mathbf{B}_{29}$	$= x_8 \mathbf{a}_1 + y_8 \mathbf{a}_2 + z_8 \mathbf{a}_3$	$= ax_8 \hat{\mathbf{x}} + by_8 \hat{\mathbf{y}} + cz_8 \hat{\mathbf{z}}$	(4a)	O IV
$\mathbf{B}_{30}$	$= -x_8 \mathbf{a}_1 - y_8 \mathbf{a}_2 + \left(z_8 + \frac{1}{2}\right) \mathbf{a}_3$	$= -ax_8 \hat{\mathbf{x}} - by_8 \hat{\mathbf{y}} + c \left(z_8 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O IV
$\mathbf{B}_{31}$	$= \left(x_8 + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_8 - \frac{1}{2}\right) \mathbf{a}_2 + z_8 \mathbf{a}_3$	$= a \left(x_8 + \frac{1}{2}\right) \hat{\mathbf{x}} - b \left(y_8 - \frac{1}{2}\right) \hat{\mathbf{y}} + cz_8 \hat{\mathbf{z}}$	(4a)	O IV
$\mathbf{B}_{32}$	$= -\left(x_8 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_8 + \frac{1}{2}\right) \mathbf{a}_2 + \left(z_8 + \frac{1}{2}\right) \mathbf{a}_3$	$= -a \left(x_8 - \frac{1}{2}\right) \hat{\mathbf{x}} + b \left(y_8 + \frac{1}{2}\right) \hat{\mathbf{y}} + c \left(z_8 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O IV
$\mathbf{B}_{33}$	$= x_9 \mathbf{a}_1 + y_9 \mathbf{a}_2 + z_9 \mathbf{a}_3$	$= ax_9 \hat{\mathbf{x}} + by_9 \hat{\mathbf{y}} + cz_9 \hat{\mathbf{z}}$	(4a)	O V
$\mathbf{B}_{34}$	$= -x_9 \mathbf{a}_1 - y_9 \mathbf{a}_2 + \left(z_9 + \frac{1}{2}\right) \mathbf{a}_3$	$= -ax_9 \hat{\mathbf{x}} - by_9 \hat{\mathbf{y}} + c \left(z_9 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O V
$\mathbf{B}_{35}$	$= \left(x_9 + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_9 - \frac{1}{2}\right) \mathbf{a}_2 + z_9 \mathbf{a}_3$	$= a \left(x_9 + \frac{1}{2}\right) \hat{\mathbf{x}} - b \left(y_9 - \frac{1}{2}\right) \hat{\mathbf{y}} + cz_9 \hat{\mathbf{z}}$	(4a)	O V
$\mathbf{B}_{36}$	$= -\left(x_9 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_9 + \frac{1}{2}\right) \mathbf{a}_2 + \left(z_9 + \frac{1}{2}\right) \mathbf{a}_3$	$= -a \left(x_9 - \frac{1}{2}\right) \hat{\mathbf{x}} + b \left(y_9 + \frac{1}{2}\right) \hat{\mathbf{y}} + c \left(z_9 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O V
$\mathbf{B}_{37}$	$= x_{10} \mathbf{a}_1 + y_{10} \mathbf{a}_2 + z_{10} \mathbf{a}_3$	$= ax_{10} \hat{\mathbf{x}} + by_{10} \hat{\mathbf{y}} + cz_{10} \hat{\mathbf{z}}$	(4a)	O VI
$\mathbf{B}_{38}$	$= -x_{10} \mathbf{a}_1 - y_{10} \mathbf{a}_2 + \left(z_{10} + \frac{1}{2}\right) \mathbf{a}_3$	$= -ax_{10} \hat{\mathbf{x}} - by_{10} \hat{\mathbf{y}} + c \left(z_{10} + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O VI
$\mathbf{B}_{39}$	$= \left(x_{10} + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_{10} - \frac{1}{2}\right) \mathbf{a}_2 + z_{10} \mathbf{a}_3$	$= a \left(x_{10} + \frac{1}{2}\right) \hat{\mathbf{x}} - b \left(y_{10} - \frac{1}{2}\right) \hat{\mathbf{y}} + cz_{10} \hat{\mathbf{z}}$	(4a)	O VI
$\mathbf{B}_{40}$	$= -\left(x_{10} - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_{10} + \frac{1}{2}\right) \mathbf{a}_2 + \left(z_{10} + \frac{1}{2}\right) \mathbf{a}_3$	$= -a \left(x_{10} - \frac{1}{2}\right) \hat{\mathbf{x}} + b \left(y_{10} + \frac{1}{2}\right) \hat{\mathbf{y}} + c \left(z_{10} + \frac{1}{2}\right) \hat{\mathbf{z}}$	(4a)	O VI

## References

- [1] B. Ollivier, R. Retoux, P. Lacorre, D. Massiot, and G. Férey, *Crystal structure of  $\kappa$ -alumina: an X-ray powder diffraction, TEM and NMR study*, J. Mater. Chem. **7**, 1049–1056 (1997), doi:10.1039/A700054E.
- [2] K. Matsuzaki, H. Yanagi, T. K. Hiramatsu, K. Nomura, and M. H. Hosono, *Field-induced current modulation in epitaxial film of deep-ultraviolet transparent oxide semiconductor  $Ga_2O_3$* , Appl. Phys. Lett. **88**, 092106 (2006), doi:10.1063/1.2179373.
- [3] S. Yoshioka, H. Hayashi, A. Kuwabara, F. Oba, K. Matsunaga, and I. Tanaka, *Structures and energetics of  $Ga_2O_3$  polymorphs*, J. Phys.: Condens. Matter **19**, 346211 (2007), doi:10.1088/0953-8984/19/34/346211.