


# Phase III $\text{Cd}_2\text{Re}_2\text{O}_7$ Structure: A2B7C2\_tI44\_98\_f\_acde\_f-001

This structure originally had the label A2B7C2.tI44\_98.f.bcde.f. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/p/XLYF>

[https://aflow.org/p/A2B7C2.tI44\\_98.f\\_acde\\_f-001](https://aflow.org/p/A2B7C2.tI44_98.f_acde_f-001)



<b>Prototype</b>	$\text{Cd}_2\text{O}_7\text{Re}_2$
<b>AFLOW prototype label</b>	A2B7C2_tI44_98_f_acde_f-001
<b>ICSD</b>	none
<b>Pearson symbol</b>	tI44
<b>Space group number</b>	98
<b>Space group symbol</b>	$I4_122$
<b>AFLOW prototype command</b>	<pre>aflow --proto=A2B7C2_tI44_98_f_acde_f-001       --params=a, c/a, z2, x3, x4, x5, x6</pre>


- $\text{Cd}_2\text{Re}_2\text{O}_7$  exhibits a number of phases. We will use the notation of (Kapcia, 2020) to describe them:
  - Phase I: Above 200K the system takes on the cubic pyrochlore ( $E8_1$ ) structure.
  - Phase II: in the range 120-200K the system is in the tetragonal  $I\bar{4}m2$  #119 structure.
  - Phase III: in the range 80-120K the system is in the tetragonal  $I4_122$  #98 structure (this structure).
  - Phase IV: (Kapcia, 2020) did a first-principles study of this system and found that below 80K Phase III develops a soft phonon mode which transforms the system into an orthorhombic  $F222$  #22 structure.

- There are many issues with all of these structures (Norman, 2020):
  - Phases II, III, and IV are all close to phase I. If we loosen the tolerance using AFLOW-SYM or FINDSYM the structures are seen to be equivalent to cubic pyrochlore.
  - Using the default tolerance, Phase II and Phase IV are equivalent.

---

### Body-centered Tetragonal primitive vectors

$$\begin{aligned}
 \mathbf{a}_1 &= -\frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}} \\
 \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}} \\
 \mathbf{a}_3 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}a \hat{\mathbf{y}} - \frac{1}{2}c \hat{\mathbf{z}}
 \end{aligned}$$




---

### Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$0$	$=$	$0$	(4a)	O I
$\mathbf{B}_2$	$\frac{3}{4} \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(4a)	O I
$\mathbf{B}_3$	$z_2 \mathbf{a}_1 + z_2 \mathbf{a}_2$	$=$	$cz_2 \hat{\mathbf{z}}$	(8c)	O II
$\mathbf{B}_4$	$(z_2 + \frac{3}{4}) \mathbf{a}_1 + (z_2 + \frac{1}{4}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{y}} + c(z_2 + \frac{1}{4}) \hat{\mathbf{z}}$	(8c)	O II
$\mathbf{B}_5$	$-(z_2 - \frac{3}{4}) \mathbf{a}_1 - (z_2 - \frac{1}{4}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{y}} - c(z_2 - \frac{1}{4}) \hat{\mathbf{z}}$	(8c)	O II
$\mathbf{B}_6$	$-z_2 \mathbf{a}_1 - z_2 \mathbf{a}_2$	$=$	$-cz_2 \hat{\mathbf{z}}$	(8c)	O II
$\mathbf{B}_7$	$x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + 2x_3 \mathbf{a}_3$	$=$	$ax_3 \hat{\mathbf{x}} + ax_3 \hat{\mathbf{y}}$	(8d)	O III
$\mathbf{B}_8$	$-x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 - 2x_3 \mathbf{a}_3$	$=$	$-ax_3 \hat{\mathbf{x}} - ax_3 \hat{\mathbf{y}}$	(8d)	O III
$\mathbf{B}_9$	$(x_3 + \frac{3}{4}) \mathbf{a}_1 - (x_3 - \frac{1}{4}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-ax_3 \hat{\mathbf{x}} + a(x_3 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(8d)	O III
$\mathbf{B}_{10}$	$-(x_3 - \frac{3}{4}) \mathbf{a}_1 + (x_3 + \frac{1}{4}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$ax_3 \hat{\mathbf{x}} - a(x_3 - \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(8d)	O III
$\mathbf{B}_{11}$	$x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2$	$=$	$-ax_4 \hat{\mathbf{x}} + ax_4 \hat{\mathbf{y}}$	(8e)	O IV
$\mathbf{B}_{12}$	$-x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2$	$=$	$ax_4 \hat{\mathbf{x}} - ax_4 \hat{\mathbf{y}}$	(8e)	O IV
$\mathbf{B}_{13}$	$-(x_4 - \frac{3}{4}) \mathbf{a}_1 - (x_4 - \frac{1}{4}) \mathbf{a}_2 - (2x_4 - \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_4 \hat{\mathbf{x}} - a(x_4 - \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(8e)	O IV
$\mathbf{B}_{14}$	$(x_4 + \frac{3}{4}) \mathbf{a}_1 + (x_4 + \frac{1}{4}) \mathbf{a}_2 + (2x_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$ax_4 \hat{\mathbf{x}} + a(x_4 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(8e)	O IV
$\mathbf{B}_{15}$	$\frac{3}{8} \mathbf{a}_1 + (x_5 + \frac{1}{8}) \mathbf{a}_2 + (x_5 + \frac{1}{4}) \mathbf{a}_3$	$=$	$ax_5 \hat{\mathbf{x}} + \frac{1}{4}a \hat{\mathbf{y}} + \frac{1}{8}c \hat{\mathbf{z}}$	(8f)	Cd I
$\mathbf{B}_{16}$	$\frac{7}{8} \mathbf{a}_1 - (x_5 - \frac{1}{8}) \mathbf{a}_2 - (x_5 - \frac{3}{4}) \mathbf{a}_3$	$=$	$-ax_5 \hat{\mathbf{x}} + \frac{3}{4}a \hat{\mathbf{y}} + \frac{1}{8}c \hat{\mathbf{z}}$	(8f)	Cd I
$\mathbf{B}_{17}$	$(x_5 + \frac{7}{8}) \mathbf{a}_1 + \frac{1}{8} \mathbf{a}_2 + (x_5 + \frac{1}{4}) \mathbf{a}_3$	$=$	$-\frac{1}{4}a \hat{\mathbf{x}} + a(x_5 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{3}{8}c \hat{\mathbf{z}}$	(8f)	Cd I
$\mathbf{B}_{18}$	$-(x_5 - \frac{7}{8}) \mathbf{a}_1 + \frac{5}{8} \mathbf{a}_2 - (x_5 - \frac{3}{4}) \mathbf{a}_3$	$=$	$\frac{1}{4}a \hat{\mathbf{x}} - a(x_5 - \frac{1}{2}) \hat{\mathbf{y}} + \frac{3}{8}c \hat{\mathbf{z}}$	(8f)	Cd I
$\mathbf{B}_{19}$	$\frac{3}{8} \mathbf{a}_1 + (x_6 + \frac{1}{8}) \mathbf{a}_2 + (x_6 + \frac{1}{4}) \mathbf{a}_3$	$=$	$ax_6 \hat{\mathbf{x}} + \frac{1}{4}a \hat{\mathbf{y}} + \frac{1}{8}c \hat{\mathbf{z}}$	(8f)	Re I
$\mathbf{B}_{20}$	$\frac{7}{8} \mathbf{a}_1 - (x_6 - \frac{1}{8}) \mathbf{a}_2 - (x_6 - \frac{3}{4}) \mathbf{a}_3$	$=$	$-ax_6 \hat{\mathbf{x}} + \frac{3}{4}a \hat{\mathbf{y}} + \frac{1}{8}c \hat{\mathbf{z}}$	(8f)	Re I
$\mathbf{B}_{21}$	$(x_6 + \frac{7}{8}) \mathbf{a}_1 + \frac{1}{8} \mathbf{a}_2 + (x_6 + \frac{1}{4}) \mathbf{a}_3$	$=$	$-\frac{1}{4}a \hat{\mathbf{x}} + a(x_6 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{3}{8}c \hat{\mathbf{z}}$	(8f)	Re I

$$\mathbf{B}_{22} = \begin{matrix} -\left(x_6 - \frac{7}{8}\right) \mathbf{a}_1 + \frac{5}{8} \mathbf{a}_2 - \\ \left(x_6 - \frac{3}{4}\right) \mathbf{a}_3 \end{matrix} = \frac{1}{4}a \hat{\mathbf{x}} - a \left(x_6 - \frac{1}{2}\right) \hat{\mathbf{y}} + \frac{3}{8}c \hat{\mathbf{z}} \quad (8f) \quad \text{Re I}$$

## References

- [1] S.-W. Huang, H.-T. Jeng, J.-Y. Lin, W. J. Chang, J. M. Chen, G. H. Lee, H. Berger, H. D. Yang, and K. S. Liang, *Electronic structure of pyrochlore  $Cd_2Re_2O_7$* , Journal of Physics: Condensed Matter **21**, 195602 (2009), doi:10.1088/0953-8984/21/19/195602.
- [2] K. J. Kapcia, M. Reedyk, M. Hajjalamdari, A. Ptok, P. Piekarczyk, A. Schulz, F. S. Razavi, R. K. Kremer, and A. M. Oleś, *Discovery of a low-temperature orthorhombic phase of the  $Cd_2Re_2O_7$  superconductor*, Phys. Rev. Res. **2**, 033108 (2020), doi:10.1103/PhysRevResearch.2.033108.

## Found in

- [1] M. R. Norman, *Crystal structure of the inversion-breaking metal  $Cd_2Re_2O_7$* , Phys. Rev. B **101**, 045117 (2020), doi:10.1103/PhysRevB.101.045117.