


Galenobismutite (PbBi_2S_4) Structure: A2BC4_oP28_62_2c_c_4c-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/PUZH>

https://aflow.org/p/A2BC4_oP28_62_2c_c_4c-001



Prototype	Bi_2PbS_4
AFLOW prototype label	A2BC4_oP28_62_2c_c_4c-001
Mineral name	galenobismutite
ICSD	158392
Pearson symbol	oP28
Space group number	62
Space group symbol	$Pnma$
AFLOW prototype command	<code>aflow --proto=A2BC4_oP28_62_2c_c_4c-001 --params=a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4,x5,z5,x6,z6,x7,z7</code>

Other compounds with this structure

BaY₂S₄, CaFe₂O₄, CaLu₂O₄, CaSc₂O₄, CaV₂O₄, CaYb₂O₄, Eu₃O₄, EuEr₂S₄, PbIn₂S₄, PbSc₂S₄, SnCe₂Se₄, SrIn₂O₄, SrTb₂O₄, SrY₂O₄, SrY₂S₄, SrYb₂O₄

- (Olson, 2007) put this structure in the $Pnam$ setting of space group #62. We used FINDSYM to transform this the standard $Pnma$ setting. We used the data taken at 1 atmosphere (100 kPa).


Simple Orthorhombic primitive vectors



$$\mathbf{a}_1 = a \hat{\mathbf{x}}$$

$$\mathbf{a}_2 = b \hat{\mathbf{y}}$$

$$\mathbf{a}_3 = c \hat{\mathbf{z}}$$



Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	$x_1 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_1 \mathbf{a}_3$	$a x_1 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + c z_1 \hat{\mathbf{z}}$	(4c)	Bi I
\mathbf{B}_2	$-(x_1 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$-a(x_1 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Bi I
\mathbf{B}_3	$-x_1 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_1 \mathbf{a}_3$	$-a x_1 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - c z_1 \hat{\mathbf{z}}$	(4c)	Bi I
\mathbf{B}_4	$(x_1 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_1 - \frac{1}{2}) \mathbf{a}_3$	$a(x_1 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c(z_1 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Bi I
\mathbf{B}_5	$x_2 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_2 \mathbf{a}_3$	$a x_2 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + c z_2 \hat{\mathbf{z}}$	(4c)	Bi II
\mathbf{B}_6	$-(x_2 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$-a(x_2 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Bi II
\mathbf{B}_7	$-x_2 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_2 \mathbf{a}_3$	$-a x_2 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - c z_2 \hat{\mathbf{z}}$	(4c)	Bi II
\mathbf{B}_8	$(x_2 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_2 - \frac{1}{2}) \mathbf{a}_3$	$a(x_2 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c(z_2 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Bi II
\mathbf{B}_9	$x_3 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_3 \mathbf{a}_3$	$a x_3 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + c z_3 \hat{\mathbf{z}}$	(4c)	Pb I
\mathbf{B}_{10}	$-(x_3 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$-a(x_3 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Pb I
\mathbf{B}_{11}	$-x_3 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_3 \mathbf{a}_3$	$-a x_3 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - c z_3 \hat{\mathbf{z}}$	(4c)	Pb I
\mathbf{B}_{12}	$(x_3 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	$a(x_3 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Pb I
\mathbf{B}_{13}	$x_4 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_4 \mathbf{a}_3$	$a x_4 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + c z_4 \hat{\mathbf{z}}$	(4c)	S I
\mathbf{B}_{14}	$-(x_4 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$-a(x_4 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	S I
\mathbf{B}_{15}	$-x_4 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_4 \mathbf{a}_3$	$-a x_4 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - c z_4 \hat{\mathbf{z}}$	(4c)	S I
\mathbf{B}_{16}	$(x_4 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$a(x_4 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	S I
\mathbf{B}_{17}	$x_5 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_5 \mathbf{a}_3$	$a x_5 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + c z_5 \hat{\mathbf{z}}$	(4c)	S II
\mathbf{B}_{18}	$-(x_5 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$-a(x_5 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	S II
\mathbf{B}_{19}	$-x_5 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_5 \mathbf{a}_3$	$-a x_5 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - c z_5 \hat{\mathbf{z}}$	(4c)	S II
\mathbf{B}_{20}	$(x_5 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	$a(x_5 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	S II
\mathbf{B}_{21}	$x_6 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_6 \mathbf{a}_3$	$a x_6 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + c z_6 \hat{\mathbf{z}}$	(4c)	S III
\mathbf{B}_{22}	$-(x_6 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	$-a(x_6 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	S III
\mathbf{B}_{23}	$-x_6 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_6 \mathbf{a}_3$	$-a x_6 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - c z_6 \hat{\mathbf{z}}$	(4c)	S III
\mathbf{B}_{24}	$(x_6 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_6 - \frac{1}{2}) \mathbf{a}_3$	$a(x_6 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c(z_6 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	S III

$$\begin{aligned}
\mathbf{B}_{25} &= x_7 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_7 \mathbf{a}_3 & = & ax_7 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + cz_7 \hat{\mathbf{z}} & (4c) & \text{S IV} \\
\mathbf{B}_{26} &= -\left(x_7 - \frac{1}{2}\right) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + \left(z_7 + \frac{1}{2}\right) \mathbf{a}_3 & = & -a\left(x_7 - \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c\left(z_7 + \frac{1}{2}\right) \hat{\mathbf{z}} & (4c) & \text{S IV} \\
\mathbf{B}_{27} &= -x_7 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_7 \mathbf{a}_3 & = & -ax_7 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - cz_7 \hat{\mathbf{z}} & (4c) & \text{S IV} \\
\mathbf{B}_{28} &= \left(x_7 + \frac{1}{2}\right) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - \left(z_7 - \frac{1}{2}\right) \mathbf{a}_3 & = & a\left(x_7 + \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c\left(z_7 - \frac{1}{2}\right) \hat{\mathbf{z}} & (4c) & \text{S IV}
\end{aligned}$$

References

- [1] L. A. Olsen, T. Balic-Zunic, E. Makovicky, A. Ullrich, and R. Miletich, *Hydrostatic compression of galenobismutite ($PbBi_2S_4$): elastic properties and high-pressure crystal chemistry*, Phys. Chem. Minerals **34**, 467–475 (2007), doi:10.1007/s00269-007-0163-9.

Found in

- [1] R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).