

# BaAs<sub>2</sub> Structure:


## A2B\_mP18\_7\_6a\_3a-001

This structure originally had the label A2B\_mP18\_7\_6a\_3a. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043

<https://aflow.org/p/34FL>


[https://aflow.org/p/A2B\\_mP18\\_7\\_6a\\_3a-001](https://aflow.org/p/A2B_mP18_7_6a_3a-001)



Prototype	As <sub>2</sub> Ba
AFLOW prototype label	A2B_mP18_7_6a_3a-001
ICSD	414139
Pearson symbol	mP18
Space group number	7
Space group symbol	<i>Pc</i>
AFLOW prototype command	<pre>aflow --proto=A2B_mP18_7_6a_3a-001 --params=a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6,x7, y7,z7,x8,y8,z8,x9,y9,z9</pre>

### Simple Monoclinic primitive vectors

$$\begin{aligned}
 \mathbf{a}_1 &= a \hat{\mathbf{x}} \\
 \mathbf{a}_2 &= b \hat{\mathbf{y}} \\
 \mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}
 \end{aligned}$$



### Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
<b>B<sub>1</sub></b>	= $x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	= $(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(2a)	As I
<b>B<sub>2</sub></b>	= $x_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_1 + c(z_1 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	As I
<b>B<sub>3</sub></b>	= $x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	= $(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(2a)	As II
<b>B<sub>4</sub></b>	= $x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_2 + c(z_2 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	As II
<b>B<sub>5</sub></b>	= $x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	= $(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(2a)	As III
<b>B<sub>6</sub></b>	= $x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_3 + c(z_3 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	As III
<b>B<sub>7</sub></b>	= $x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	= $(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \sin \beta \hat{\mathbf{z}}$	(2a)	As IV
<b>B<sub>8</sub></b>	= $x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_4 + c(z_4 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	As IV
<b>B<sub>9</sub></b>	= $x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	= $(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \sin \beta \hat{\mathbf{z}}$	(2a)	As V
<b>B<sub>10</sub></b>	= $x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_5 + c(z_5 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	As V
<b>B<sub>11</sub></b>	= $x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	= $(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \sin \beta \hat{\mathbf{z}}$	(2a)	As VI
<b>B<sub>12</sub></b>	= $x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_6 + c(z_6 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	As VI
<b>B<sub>13</sub></b>	= $x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	= $(ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \sin \beta \hat{\mathbf{z}}$	(2a)	Ba I
<b>B<sub>14</sub></b>	= $x_7 \mathbf{a}_1 - y_7 \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_7 + c(z_7 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	Ba I
<b>B<sub>15</sub></b>	= $x_8 \mathbf{a}_1 + y_8 \mathbf{a}_2 + z_8 \mathbf{a}_3$	= $(ax_8 + cz_8 \cos \beta) \hat{\mathbf{x}} + by_8 \hat{\mathbf{y}} + cz_8 \sin \beta \hat{\mathbf{z}}$	(2a)	Ba II
<b>B<sub>16</sub></b>	= $x_8 \mathbf{a}_1 - y_8 \mathbf{a}_2 + (z_8 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_8 + c(z_8 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_8 \hat{\mathbf{y}} + c(z_8 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	Ba II
<b>B<sub>17</sub></b>	= $x_9 \mathbf{a}_1 + y_9 \mathbf{a}_2 + z_9 \mathbf{a}_3$	= $(ax_9 + cz_9 \cos \beta) \hat{\mathbf{x}} + by_9 \hat{\mathbf{y}} + cz_9 \sin \beta \hat{\mathbf{z}}$	(2a)	Ba III
<b>B<sub>18</sub></b>	= $x_9 \mathbf{a}_1 - y_9 \mathbf{a}_2 + (z_9 + \frac{1}{2}) \mathbf{a}_3$	= $(ax_9 + c(z_9 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_9 \hat{\mathbf{y}} + c(z_9 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(2a)	Ba III

## References

- [1] F. Emmerling, D. Petri, and C. Röhr, *Neue Arsenide mit As<sup>-</sup>-Ketten und -Ringen: BaAs<sub>2</sub> und A<sup>I</sup>Ba<sub>2</sub>As<sub>5</sub> (A<sup>I</sup> = K, Rb)*, Z. Anorganische und Allgemeine Chemie **630**, 2490–2501 (2004), doi:10.1002/zaac.200400257.

## Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.