


Cu₃(P₂O₆OH)₂ Structure: A3B12C2D4_aP21_2_ai_6i_i_2i-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/L1KQ>

https://aflow.org/p/A3B12C2D4_aP21_2_ai_6i_i_2i-001




Prototype	Cu ₃ O ₁₂ (OH) ₂ P ₄
AFLOW prototype label	A3B12C2D4_aP21_2_ai_6i_i_2i-001
ICSD	170128
Pearson symbol	aP21
Space group number	2
Space group symbol	$P\bar{1}$
AFLOW prototype command	<pre>aflow --proto=A3B12C2D4_aP21_2_ai_6i_i_2i-001 --params=a,b/a,c/a,α,β,γ,x₂,y₂,z₂,x₃,y₃,z₃,x₄,y₄,z₄,x₅,y₅,z₅,x₆,y₆,z₆,x₇,y₇, z₇,x₈,y₈,z₈,x₉,y₉,z₉,x₁₀,y₁₀,z₁₀,x₁₁,y₁₁,z₁₁</pre>

- The positions of the hydrogen atoms in the OH radicals were not determined. While we list the radical as a separate species, OH I, (Baies, 2005) simply list it as O7.
- The positions of the oxygen atoms in the ICSD entry do not precisely match the positions in Table 2 of (Baies, 2005).

Triclinic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= a \hat{\mathbf{x}} \\
\mathbf{a}_2 &= b \cos \gamma \hat{\mathbf{x}} + b \sin \gamma \hat{\mathbf{y}} \\
\mathbf{a}_3 &= c_x \hat{\mathbf{x}} + c_y \hat{\mathbf{y}} + c_z \hat{\mathbf{z}} \\
c_x &= c \cos \beta \\
c_y &= c(\cos \alpha - \cos \beta \cos \gamma) / \sin \gamma \\
c_z &= \sqrt{c^2 - c_x^2 - c_y^2}
\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	0	$=$	0	(1a)	Cu I
\mathbf{B}_2	$x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$(ax_2 + by_2 \cos \gamma + c_x z_2) \hat{\mathbf{x}} + (by_2 \sin \gamma + c_y z_2) \hat{\mathbf{y}} + c_z z_2 \hat{\mathbf{z}}$	(2i)	Cu II
\mathbf{B}_3	$-x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 - z_2 \mathbf{a}_3$	$=$	$-(ax_2 + by_2 \cos \gamma + c_x z_2) \hat{\mathbf{x}} - (by_2 \sin \gamma + c_y z_2) \hat{\mathbf{y}} - c_z z_2 \hat{\mathbf{z}}$	(2i)	Cu II
\mathbf{B}_4	$x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$(ax_3 + by_3 \cos \gamma + c_x z_3) \hat{\mathbf{x}} + (by_3 \sin \gamma + c_y z_3) \hat{\mathbf{y}} + c_z z_3 \hat{\mathbf{z}}$	(2i)	O I
\mathbf{B}_5	$-x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 - z_3 \mathbf{a}_3$	$=$	$-(ax_3 + by_3 \cos \gamma + c_x z_3) \hat{\mathbf{x}} - (by_3 \sin \gamma + c_y z_3) \hat{\mathbf{y}} - c_z z_3 \hat{\mathbf{z}}$	(2i)	O I
\mathbf{B}_6	$x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$(ax_4 + by_4 \cos \gamma + c_x z_4) \hat{\mathbf{x}} + (by_4 \sin \gamma + c_y z_4) \hat{\mathbf{y}} + c_z z_4 \hat{\mathbf{z}}$	(2i)	O II
\mathbf{B}_7	$-x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-(ax_4 + by_4 \cos \gamma + c_x z_4) \hat{\mathbf{x}} - (by_4 \sin \gamma + c_y z_4) \hat{\mathbf{y}} - c_z z_4 \hat{\mathbf{z}}$	(2i)	O II
\mathbf{B}_8	$x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$(ax_5 + by_5 \cos \gamma + c_x z_5) \hat{\mathbf{x}} + (by_5 \sin \gamma + c_y z_5) \hat{\mathbf{y}} + c_z z_5 \hat{\mathbf{z}}$	(2i)	O III
\mathbf{B}_9	$-x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 - z_5 \mathbf{a}_3$	$=$	$-(ax_5 + by_5 \cos \gamma + c_x z_5) \hat{\mathbf{x}} - (by_5 \sin \gamma + c_y z_5) \hat{\mathbf{y}} - c_z z_5 \hat{\mathbf{z}}$	(2i)	O III
\mathbf{B}_{10}	$x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	$=$	$(ax_6 + by_6 \cos \gamma + c_x z_6) \hat{\mathbf{x}} + (by_6 \sin \gamma + c_y z_6) \hat{\mathbf{y}} + c_z z_6 \hat{\mathbf{z}}$	(2i)	O IV
\mathbf{B}_{11}	$-x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 - z_6 \mathbf{a}_3$	$=$	$-(ax_6 + by_6 \cos \gamma + c_x z_6) \hat{\mathbf{x}} - (by_6 \sin \gamma + c_y z_6) \hat{\mathbf{y}} - c_z z_6 \hat{\mathbf{z}}$	(2i)	O IV
\mathbf{B}_{12}	$x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	$=$	$(ax_7 + by_7 \cos \gamma + c_x z_7) \hat{\mathbf{x}} + (by_7 \sin \gamma + c_y z_7) \hat{\mathbf{y}} + c_z z_7 \hat{\mathbf{z}}$	(2i)	O V
\mathbf{B}_{13}	$-x_7 \mathbf{a}_1 - y_7 \mathbf{a}_2 - z_7 \mathbf{a}_3$	$=$	$-(ax_7 + by_7 \cos \gamma + c_x z_7) \hat{\mathbf{x}} - (by_7 \sin \gamma + c_y z_7) \hat{\mathbf{y}} - c_z z_7 \hat{\mathbf{z}}$	(2i)	O V
\mathbf{B}_{14}	$x_8 \mathbf{a}_1 + y_8 \mathbf{a}_2 + z_8 \mathbf{a}_3$	$=$	$(ax_8 + by_8 \cos \gamma + c_x z_8) \hat{\mathbf{x}} + (by_8 \sin \gamma + c_y z_8) \hat{\mathbf{y}} + c_z z_8 \hat{\mathbf{z}}$	(2i)	O VI
\mathbf{B}_{15}	$-x_8 \mathbf{a}_1 - y_8 \mathbf{a}_2 - z_8 \mathbf{a}_3$	$=$	$-(ax_8 + by_8 \cos \gamma + c_x z_8) \hat{\mathbf{x}} - (by_8 \sin \gamma + c_y z_8) \hat{\mathbf{y}} - c_z z_8 \hat{\mathbf{z}}$	(2i)	O VI
\mathbf{B}_{16}	$x_9 \mathbf{a}_1 + y_9 \mathbf{a}_2 + z_9 \mathbf{a}_3$	$=$	$(ax_9 + by_9 \cos \gamma + c_x z_9) \hat{\mathbf{x}} + (by_9 \sin \gamma + c_y z_9) \hat{\mathbf{y}} + c_z z_9 \hat{\mathbf{z}}$	(2i)	OH I
\mathbf{B}_{17}	$-x_9 \mathbf{a}_1 - y_9 \mathbf{a}_2 - z_9 \mathbf{a}_3$	$=$	$-(ax_9 + by_9 \cos \gamma + c_x z_9) \hat{\mathbf{x}} - (by_9 \sin \gamma + c_y z_9) \hat{\mathbf{y}} - c_z z_9 \hat{\mathbf{z}}$	(2i)	OH I
\mathbf{B}_{18}	$x_{10} \mathbf{a}_1 + y_{10} \mathbf{a}_2 + z_{10} \mathbf{a}_3$	$=$	$(ax_{10} + by_{10} \cos \gamma + c_x z_{10}) \hat{\mathbf{x}} + (by_{10} \sin \gamma + c_y z_{10}) \hat{\mathbf{y}} + c_z z_{10} \hat{\mathbf{z}}$	(2i)	P I
\mathbf{B}_{19}	$-x_{10} \mathbf{a}_1 - y_{10} \mathbf{a}_2 - z_{10} \mathbf{a}_3$	$=$	$-(ax_{10} + by_{10} \cos \gamma + c_x z_{10}) \hat{\mathbf{x}} - (by_{10} \sin \gamma + c_y z_{10}) \hat{\mathbf{y}} - c_z z_{10} \hat{\mathbf{z}}$	(2i)	P I

$$\mathbf{B}_{20} = x_{11} \mathbf{a}_1 + y_{11} \mathbf{a}_2 + z_{11} \mathbf{a}_3 = (ax_{11} + by_{11} \cos \gamma + c_x z_{11}) \hat{\mathbf{x}} + (by_{11} \sin \gamma + c_y z_{11}) \hat{\mathbf{y}} + c_z z_{11} \hat{\mathbf{z}} \quad (2i) \quad \text{P II}$$

$$\mathbf{B}_{21} = -x_{11} \mathbf{a}_1 - y_{11} \mathbf{a}_2 - z_{11} \mathbf{a}_3 = -(ax_{11} + by_{11} \cos \gamma + c_x z_{11}) \hat{\mathbf{x}} - (by_{11} \sin \gamma + c_y z_{11}) \hat{\mathbf{y}} - c_z z_{11} \hat{\mathbf{z}} \quad (2i) \quad \text{P II}$$

References

- [1] R. Baies, V. Caignaert, V. Pralong, and B. Raveau, *Copper Hydroxydiphosphate with a One-Dimensional Arrangement of Copper Polyhedra: $\text{Cu}_3[\text{P}_2\text{O}_6\text{OH}]_2$* , *Inorganic Chemistry* **44**, 2376–2380 (2005), doi:10.1021/ic0485209.