


Ba₃Cr₂O₈ Structure: A3B2C8_hR13_166_ac_c_ch-002

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/7UDV>

https://aflow.org/p/A3B2C8_hR13_166_ac_c_ch-002



Prototype	Ba ₃ Cr ₂ O ₈
AFLOW prototype label	A3B2C8_hR13_166_ac_c_ch-002
ICSD	159409
Pearson symbol	hR13
Space group number	166
Space group symbol	$R\bar{3}m$
AFLOW prototype command	<code>aflow --proto=A3B2C8_hR13_166_ac_c_ch-002 --params=a, c/a, x₂, x₃, x₄, x₅, z₅</code>


Other compounds with this structure

Sr₃Cr₂O₈

- This is the ternary version of the D_{8h} (Fe₇W₆) structure. The structure given by (Nakajima, 2008) does not appear in the ICSD. We give the ICSD entry for the structure determined by (Aczel, 2008).
- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{1}{\sqrt{3}}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\ \mathbf{a}_3 &= -\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	0	$=$	0	(1a)	Ba I
\mathbf{B}_2	$x_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + x_2 \mathbf{a}_3$	$=$	$cx_2 \hat{\mathbf{z}}$	(2c)	Ba II
\mathbf{B}_3	$-x_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 - x_2 \mathbf{a}_3$	$=$	$-cx_2 \hat{\mathbf{z}}$	(2c)	Ba II
\mathbf{B}_4	$x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + x_3 \mathbf{a}_3$	$=$	$cx_3 \hat{\mathbf{z}}$	(2c)	Cr I
\mathbf{B}_5	$-x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 - x_3 \mathbf{a}_3$	$=$	$-cx_3 \hat{\mathbf{z}}$	(2c)	Cr I
\mathbf{B}_6	$x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + x_4 \mathbf{a}_3$	$=$	$cx_4 \hat{\mathbf{z}}$	(2c)	O I
\mathbf{B}_7	$-x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 - x_4 \mathbf{a}_3$	$=$	$-cx_4 \hat{\mathbf{z}}$	(2c)	O I
\mathbf{B}_8	$x_5 \mathbf{a}_1 + x_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_5 - z_5) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_5 - z_5) \hat{\mathbf{y}} + \frac{1}{3}c(2x_5 + z_5) \hat{\mathbf{z}}$	(6h)	O II
\mathbf{B}_9	$z_5 \mathbf{a}_1 + x_5 \mathbf{a}_2 + x_5 \mathbf{a}_3$	$=$	$-\frac{1}{2}a(x_5 - z_5) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_5 - z_5) \hat{\mathbf{y}} + \frac{1}{3}c(2x_5 + z_5) \hat{\mathbf{z}}$	(6h)	O II
\mathbf{B}_{10}	$x_5 \mathbf{a}_1 + z_5 \mathbf{a}_2 + x_5 \mathbf{a}_3$	$=$	$-\frac{1}{\sqrt{3}}a(x_5 - z_5) \hat{\mathbf{y}} + \frac{1}{3}c(2x_5 + z_5) \hat{\mathbf{z}}$	(6h)	O II
\mathbf{B}_{11}	$-z_5 \mathbf{a}_1 - x_5 \mathbf{a}_2 - x_5 \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_5 - z_5) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_5 - z_5) \hat{\mathbf{y}} - \frac{1}{3}c(2x_5 + z_5) \hat{\mathbf{z}}$	(6h)	O II
\mathbf{B}_{12}	$-x_5 \mathbf{a}_1 - x_5 \mathbf{a}_2 - z_5 \mathbf{a}_3$	$=$	$-\frac{1}{2}a(x_5 - z_5) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_5 - z_5) \hat{\mathbf{y}} - \frac{1}{3}c(2x_5 + z_5) \hat{\mathbf{z}}$	(6h)	O II
\mathbf{B}_{13}	$-x_5 \mathbf{a}_1 - z_5 \mathbf{a}_2 - x_5 \mathbf{a}_3$	$=$	$\frac{1}{\sqrt{3}}a(x_5 - z_5) \hat{\mathbf{y}} - \frac{1}{3}c(2x_5 + z_5) \hat{\mathbf{z}}$	(6h)	O II

References

- [1] T. Nakajima, H. Mitamura, and Y. Ueda, *Singlet Ground State and Magnetic Interactions in New Spin Dimer System $Ba_3Cr_2O_8$* , J. Phys. Soc. Jpn. **75**, 054706 (2006), doi:10.1143/JPSJ.75.054706.
- [2] A. A. Aczel, H. A. Dabkowska, P. R. Provencher, and G. M. Luke, *Crystal growth and characterization of the new spin dimer system $Ba_3Cr_2O_8$* , J. Crystal Growth **310**, 870–873 (2008), doi:10.1016/j.jcrysgro.2007.12.030.

Found in

- [1] C. Xu, S. Zhai, L. Ye, X. Wu, and K. Yang, *X-ray diffraction studies of $Sr_3Cr_2O_8$ and $Ba_3Cr_2O_8$ at high pressures*, Solid State Commun. **200**, 5–8 (2014), doi:10.1016/j.ssc.2014.09.010.