


# Chrysotile $\text{Mg}_3\text{Si}_2\text{O}_5(\text{OH})_4$ Structure: A3B5C4D2\_mC56\_9\_3a\_5a\_4a\_2a-001

This structure originally had the label A3B5C4D2\_mC56\_9\_3a\_5a\_4a\_2a. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/p/BT10>

[https://aflow.org/p/A3B5C4D2\\_mC56\\_9\\_3a\\_5a\\_4a\\_2a-001](https://aflow.org/p/A3B5C4D2_mC56_9_3a_5a_4a_2a-001)





<b>Prototype</b>	$\text{Mg}_3\text{O}_5(\text{OH})_4\text{Si}_2$
<b>AFLOW prototype label</b>	A3B5C4D2_mC56_9_3a_5a_4a_2a-001
<b>Mineral name</b>	chrysotile
<b>ICSD</b>	413633
<b>Pearson symbol</b>	mC56
<b>Space group number</b>	9
<b>Space group symbol</b>	$Cc$
<b>AFLOW prototype command</b>	<pre>aflow --proto=A3B5C4D2_mC56_9_3a_5a_4a_2a-001 --params=a,b/a,c/a,\beta,x_1,y_1,z_1,x_2,y_2,z_2,x_3,y_3,z_3,x_4,y_4,z_4,x_5,y_5,z_5,x_6,y_6,z_6,x_7, y_7,z_7,x_8,y_8,z_8,x_9,y_9,z_9,x_{10},y_{10},z_{10},x_{11},y_{11},z_{11},x_{12},y_{12},z_{12},x_{13},y_{13},z_{13},x_{14},y_{14},z_{14}</pre>

- Chrysotile is more commonly known as “white asbestos.” Chrysotile sheets typically curl into tubular fibers and the crystal structure is difficult to determine. (Yada, 1967) has a partial list of the experiments performed to determine this structure.
- This structure differs from (Warren, 1931),  $S4_5$ , halving the size of the unit cell and removing the inversion site.
- For this prototype the OH molecules are centered on (4a) Wyckoff positions.

## Base-centered Monoclinic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}\end{aligned}$$



## Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$(x_1 - y_1) \mathbf{a}_1 + (x_1 + y_1) \mathbf{a}_2 + z_1 \mathbf{a}_3$	$(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(4a)	Mg I
$\mathbf{B}_2$	$(x_1 + y_1) \mathbf{a}_1 + (x_1 - y_1) \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$(ax_1 + c(z_1 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	Mg I
$\mathbf{B}_3$	$(x_2 - y_2) \mathbf{a}_1 + (x_2 + y_2) \mathbf{a}_2 + z_2 \mathbf{a}_3$	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(4a)	Mg II
$\mathbf{B}_4$	$(x_2 + y_2) \mathbf{a}_1 + (x_2 - y_2) \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$(ax_2 + c(z_2 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	Mg II
$\mathbf{B}_5$	$(x_3 - y_3) \mathbf{a}_1 + (x_3 + y_3) \mathbf{a}_2 + z_3 \mathbf{a}_3$	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(4a)	Mg III
$\mathbf{B}_6$	$(x_3 + y_3) \mathbf{a}_1 + (x_3 - y_3) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$(ax_3 + c(z_3 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	Mg III
$\mathbf{B}_7$	$(x_4 - y_4) \mathbf{a}_1 + (x_4 + y_4) \mathbf{a}_2 + z_4 \mathbf{a}_3$	$(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \sin \beta \hat{\mathbf{z}}$	(4a)	O I
$\mathbf{B}_8$	$(x_4 + y_4) \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$(ax_4 + c(z_4 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	O I
$\mathbf{B}_9$	$(x_5 - y_5) \mathbf{a}_1 + (x_5 + y_5) \mathbf{a}_2 + z_5 \mathbf{a}_3$	$(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \sin \beta \hat{\mathbf{z}}$	(4a)	O II
$\mathbf{B}_{10}$	$(x_5 + y_5) \mathbf{a}_1 + (x_5 - y_5) \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$(ax_5 + c(z_5 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	O II
$\mathbf{B}_{11}$	$(x_6 - y_6) \mathbf{a}_1 + (x_6 + y_6) \mathbf{a}_2 + z_6 \mathbf{a}_3$	$(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \sin \beta \hat{\mathbf{z}}$	(4a)	O III
$\mathbf{B}_{12}$	$(x_6 + y_6) \mathbf{a}_1 + (x_6 - y_6) \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	$(ax_6 + c(z_6 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	O III
$\mathbf{B}_{13}$	$(x_7 - y_7) \mathbf{a}_1 + (x_7 + y_7) \mathbf{a}_2 + z_7 \mathbf{a}_3$	$(ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \sin \beta \hat{\mathbf{z}}$	(4a)	O IV
$\mathbf{B}_{14}$	$(x_7 + y_7) \mathbf{a}_1 + (x_7 - y_7) \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	$(ax_7 + c(z_7 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	O IV
$\mathbf{B}_{15}$	$(x_8 - y_8) \mathbf{a}_1 + (x_8 + y_8) \mathbf{a}_2 + z_8 \mathbf{a}_3$	$(ax_8 + cz_8 \cos \beta) \hat{\mathbf{x}} + by_8 \hat{\mathbf{y}} + cz_8 \sin \beta \hat{\mathbf{z}}$	(4a)	O V
$\mathbf{B}_{16}$	$(x_8 + y_8) \mathbf{a}_1 + (x_8 - y_8) \mathbf{a}_2 + (z_8 + \frac{1}{2}) \mathbf{a}_3$	$(ax_8 + c(z_8 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_8 \hat{\mathbf{y}} + c(z_8 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	O V
$\mathbf{B}_{17}$	$(x_9 - y_9) \mathbf{a}_1 + (x_9 + y_9) \mathbf{a}_2 + z_9 \mathbf{a}_3$	$(ax_9 + cz_9 \cos \beta) \hat{\mathbf{x}} + by_9 \hat{\mathbf{y}} + cz_9 \sin \beta \hat{\mathbf{z}}$	(4a)	OH I

<b>B<sub>18</sub></b>	$= (x_9 + y_9) \mathbf{a}_1 + (x_9 - y_9) \mathbf{a}_2 + (z_9 + \frac{1}{2}) \mathbf{a}_3$	$= (ax_9 + c(z_9 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_9 \hat{\mathbf{y}} + c(z_9 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	OH I
<b>B<sub>19</sub></b>	$= (x_{10} - y_{10}) \mathbf{a}_1 + (x_{10} + y_{10}) \mathbf{a}_2 + z_{10} \mathbf{a}_3$	$= (ax_{10} + cz_{10} \cos \beta) \hat{\mathbf{x}} + by_{10} \hat{\mathbf{y}} + cz_{10} \sin \beta \hat{\mathbf{z}}$	(4a)	OH II
<b>B<sub>20</sub></b>	$= (x_{10} + y_{10}) \mathbf{a}_1 + (x_{10} - y_{10}) \mathbf{a}_2 + (z_{10} + \frac{1}{2}) \mathbf{a}_3$	$= (ax_{10} + c(z_{10} + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_{10} \hat{\mathbf{y}} + c(z_{10} + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	OH II
<b>B<sub>21</sub></b>	$= (x_{11} - y_{11}) \mathbf{a}_1 + (x_{11} + y_{11}) \mathbf{a}_2 + z_{11} \mathbf{a}_3$	$= (ax_{11} + cz_{11} \cos \beta) \hat{\mathbf{x}} + by_{11} \hat{\mathbf{y}} + cz_{11} \sin \beta \hat{\mathbf{z}}$	(4a)	OH III
<b>B<sub>22</sub></b>	$= (x_{11} + y_{11}) \mathbf{a}_1 + (x_{11} - y_{11}) \mathbf{a}_2 + (z_{11} + \frac{1}{2}) \mathbf{a}_3$	$= (ax_{11} + c(z_{11} + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_{11} \hat{\mathbf{y}} + c(z_{11} + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	OH III
<b>B<sub>23</sub></b>	$= (x_{12} - y_{12}) \mathbf{a}_1 + (x_{12} + y_{12}) \mathbf{a}_2 + z_{12} \mathbf{a}_3$	$= (ax_{12} + cz_{12} \cos \beta) \hat{\mathbf{x}} + by_{12} \hat{\mathbf{y}} + cz_{12} \sin \beta \hat{\mathbf{z}}$	(4a)	OH IV
<b>B<sub>24</sub></b>	$= (x_{12} + y_{12}) \mathbf{a}_1 + (x_{12} - y_{12}) \mathbf{a}_2 + (z_{12} + \frac{1}{2}) \mathbf{a}_3$	$= (ax_{12} + c(z_{12} + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_{12} \hat{\mathbf{y}} + c(z_{12} + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	OH IV
<b>B<sub>25</sub></b>	$= (x_{13} - y_{13}) \mathbf{a}_1 + (x_{13} + y_{13}) \mathbf{a}_2 + z_{13} \mathbf{a}_3$	$= (ax_{13} + cz_{13} \cos \beta) \hat{\mathbf{x}} + by_{13} \hat{\mathbf{y}} + cz_{13} \sin \beta \hat{\mathbf{z}}$	(4a)	Si I
<b>B<sub>26</sub></b>	$= (x_{13} + y_{13}) \mathbf{a}_1 + (x_{13} - y_{13}) \mathbf{a}_2 + (z_{13} + \frac{1}{2}) \mathbf{a}_3$	$= (ax_{13} + c(z_{13} + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_{13} \hat{\mathbf{y}} + c(z_{13} + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	Si I
<b>B<sub>27</sub></b>	$= (x_{14} - y_{14}) \mathbf{a}_1 + (x_{14} + y_{14}) \mathbf{a}_2 + z_{14} \mathbf{a}_3$	$= (ax_{14} + cz_{14} \cos \beta) \hat{\mathbf{x}} + by_{14} \hat{\mathbf{y}} + cz_{14} \sin \beta \hat{\mathbf{z}}$	(4a)	Si II
<b>B<sub>28</sub></b>	$= (x_{14} + y_{14}) \mathbf{a}_1 + (x_{14} - y_{14}) \mathbf{a}_2 + (z_{14} + \frac{1}{2}) \mathbf{a}_3$	$= (ax_{14} + c(z_{14} + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_{14} \hat{\mathbf{y}} + c(z_{14} + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(4a)	Si II

## References

- [1] G. Falini, E. Foresti, M. Gazzano, A. F. Gualtieri, M. Leoni, I. G. Lesci, and N. Roveri, *Tubular-Shaped Stoichiometric Chrysotile Nanocrystals*, Chem. Eur. J. **10**, 3043–3049 (2004), doi:10.1002/chem.200305685.
- [2] K. Yada, *Study of Chrysotile Asbestos by a High Resolution Electron Microscope*, Acta Cryst. **23**, 704–707 (1967), doi:10.1107/S0365110X67003524.
- [3] B. E. Warren and W. L. Bragg, *The Structure of Chrysotile H<sub>4</sub>Mg<sub>3</sub>Si<sub>2</sub>O<sub>9</sub>*, Z. Krystallogr. **76**, 201–210 (1931), doi:10.1524/zkri.1931.76.1.201.