


Disordered YBO₃ Structure: A3B5C_hP18_194_h_fh_a-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://afLOW.org/p/3718>

https://afLOW.org/p/A3B5C_hP18_194_h_fh_a-001



| | |
|-------------------------|---|
| Prototype | BO ₃ Y |
| AFLOW prototype label | A3B5C_hP18_194_h_fh_a-001 |
| ICSD | 27931 |
| Pearson symbol | hP18 |
| Space group number | 194 |
| Space group symbol | <i>P6₃/mmc</i> |
| AFLOW prototype command | <code>afLOW --proto=A3B5C_hP18_194_h_fh_a-001 --params=a, c/a, z₂, x₃, x₄</code> |

Other compounds with this structure


DyBO₃, ErBO₃, EuBO₃, GdBO₃, HoBO₃, LuBO₃, SmBO₃, TmBO₃, YbBO₃

- (Newnham, 1963) found two possible structures for TmBO₃ and YBO₃:
 - This structure, with a compact hexagonal cell and partially disordered boron and oxygen atoms, and
 - a completely ordered structure with a larger hexagonal cell.

- In the current structure only 1/3 of the boron and oxygen (6h) sites are occupied.

Hexagonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

| | Lattice coordinates | = | Cartesian coordinates | Wyckoff position | Atom type |
|-------------------|--|---|--|------------------|-----------|
| \mathbf{B}_1 | 0 | = | 0 | (2a) | Y I |
| \mathbf{B}_2 | $\frac{1}{2} \mathbf{a}_3$ | = | $\frac{1}{2}c \hat{\mathbf{z}}$ | (2a) | Y I |
| \mathbf{B}_3 | $\frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + z_2 \mathbf{a}_3$ | = | $\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$ | (4f) | O I |
| \mathbf{B}_4 | $\frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$ | = | $\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$ | (4f) | O I |
| \mathbf{B}_5 | $\frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 - z_2 \mathbf{a}_3$ | = | $\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$ | (4f) | O I |
| \mathbf{B}_6 | $\frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 - (z_2 - \frac{1}{2}) \mathbf{a}_3$ | = | $\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} - c(z_2 - \frac{1}{2}) \hat{\mathbf{z}}$ | (4f) | O I |
| \mathbf{B}_7 | $x_3 \mathbf{a}_1 + 2x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$ | = | $\frac{3}{2}ax_3 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$ | (6h) | B I |
| \mathbf{B}_8 | $-2x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$ | = | $-\frac{3}{2}ax_3 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$ | (6h) | B I |
| \mathbf{B}_9 | $x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$ | = | $-\sqrt{3}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$ | (6h) | B I |
| \mathbf{B}_{10} | $-x_3 \mathbf{a}_1 - 2x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$ | = | $-\frac{3}{2}ax_3 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$ | (6h) | B I |
| \mathbf{B}_{11} | $2x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$ | = | $\frac{3}{2}ax_3 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$ | (6h) | B I |
| \mathbf{B}_{12} | $-x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$ | = | $\sqrt{3}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$ | (6h) | B I |
| \mathbf{B}_{13} | $x_4 \mathbf{a}_1 + 2x_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$ | = | $\frac{3}{2}ax_4 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$ | (6h) | O II |
| \mathbf{B}_{14} | $-2x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$ | = | $-\frac{3}{2}ax_4 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$ | (6h) | O II |
| \mathbf{B}_{15} | $x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$ | = | $-\sqrt{3}ax_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$ | (6h) | O II |
| \mathbf{B}_{16} | $-x_4 \mathbf{a}_1 - 2x_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$ | = | $-\frac{3}{2}ax_4 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$ | (6h) | O II |
| \mathbf{B}_{17} | $2x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$ | = | $\frac{3}{2}ax_4 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$ | (6h) | O II |
| \mathbf{B}_{18} | $-x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$ | = | $\sqrt{3}ax_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$ | (6h) | O II |

References

- [1] R. E. Newnham, M. J. Redman, and R. P. Santoro, *Crystal Structure of Yttrium and Other Rare-Earth Borates*, J. Am. Ceram. Soc. **46**, 253–256 (1963), doi:10.1111/j.1151-2916.1963.tb11721.x.