


Cs₃GeTe₃ (Cs₆Ge₂Te₆) Structure: A3BC3_mC56_15_2e2f_f_3f-001

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Osos, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/DE47>

https://aflow.org/prototype-encyclopedia/A3BC3_mC56_15_2e2f_f_3f-001




Prototype	Cs ₃ GeTe ₃
AFLOW prototype label	A3BC3_mC56_15_2e2f_f_3f-001
ICSD	89683
CCDC	1649342
Pearson symbol	mC56
Space group number	15
Space group symbol	C2/c
AFLOW prototype command	<pre>aflow --proto=A3BC3_mC56_15_2e2f_f_3f-001 --params=a, b/a, c/a, β, y1, y2, x3, y3, z3, x4, y4, z4, x5, y5, z5, x6, y6, z6, x7, y7, z7, x8, y8, z8</pre>

Other compounds with this structure

Cs₃GeSe₃, Cs₃SnTe₃, K₃GeTe₃

Base-centered Monoclinic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= -y_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{4}c \cos \beta \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + \frac{1}{4}c \sin \beta \hat{\mathbf{z}}$	(4e)	Cs I
$\mathbf{B}_2$	$= y_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{3}{4}c \cos \beta \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + \frac{3}{4}c \sin \beta \hat{\mathbf{z}}$	(4e)	Cs I
$\mathbf{B}_3$	$= -y_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{4}c \cos \beta \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + \frac{1}{4}c \sin \beta \hat{\mathbf{z}}$	(4e)	Cs II
$\mathbf{B}_4$	$= y_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{3}{4}c \cos \beta \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + \frac{3}{4}c \sin \beta \hat{\mathbf{z}}$	(4e)	Cs II
$\mathbf{B}_5$	$= (x_3 - y_3) \mathbf{a}_1 + (x_3 + y_3) \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(8f)	Cs III
$\mathbf{B}_6$	$= -(x_3 + y_3) \mathbf{a}_1 - (x_3 - y_3) \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	$=$	$-(ax_3 + c(z_3 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Cs III
$\mathbf{B}_7$	$= -(x_3 - y_3) \mathbf{a}_1 - (x_3 + y_3) \mathbf{a}_2 - z_3 \mathbf{a}_3$	$=$	$-(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} - cz_3 \sin \beta \hat{\mathbf{z}}$	(8f)	Cs III
$\mathbf{B}_8$	$= (x_3 + y_3) \mathbf{a}_1 + (x_3 - y_3) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$(ax_3 + c(z_3 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Cs III
$\mathbf{B}_9$	$= (x_4 - y_4) \mathbf{a}_1 + (x_4 + y_4) \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \sin \beta \hat{\mathbf{z}}$	(8f)	Cs IV
$\mathbf{B}_{10}$	$= -(x_4 + y_4) \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$=$	$-(ax_4 + c(z_4 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Cs IV
$\mathbf{B}_{11}$	$= -(x_4 - y_4) \mathbf{a}_1 - (x_4 + y_4) \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} - cz_4 \sin \beta \hat{\mathbf{z}}$	(8f)	Cs IV
$\mathbf{B}_{12}$	$= (x_4 + y_4) \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$(ax_4 + c(z_4 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Cs IV
$\mathbf{B}_{13}$	$= (x_5 - y_5) \mathbf{a}_1 + (x_5 + y_5) \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \sin \beta \hat{\mathbf{z}}$	(8f)	Ge I
$\mathbf{B}_{14}$	$= -(x_5 + y_5) \mathbf{a}_1 - (x_5 - y_5) \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	$=$	$-(ax_5 + c(z_5 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ge I
$\mathbf{B}_{15}$	$= -(x_5 - y_5) \mathbf{a}_1 - (x_5 + y_5) \mathbf{a}_2 - z_5 \mathbf{a}_3$	$=$	$-(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} - cz_5 \sin \beta \hat{\mathbf{z}}$	(8f)	Ge I
$\mathbf{B}_{16}$	$= (x_5 + y_5) \mathbf{a}_1 + (x_5 - y_5) \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$=$	$(ax_5 + c(z_5 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ge I
$\mathbf{B}_{17}$	$= (x_6 - y_6) \mathbf{a}_1 + (x_6 + y_6) \mathbf{a}_2 + z_6 \mathbf{a}_3$	$=$	$(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \sin \beta \hat{\mathbf{z}}$	(8f)	Te I
$\mathbf{B}_{18}$	$= -(x_6 + y_6) \mathbf{a}_1 - (x_6 - y_6) \mathbf{a}_2 - (z_6 - \frac{1}{2}) \mathbf{a}_3$	$=$	$-(ax_6 + c(z_6 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} - c(z_6 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Te I

$$\begin{aligned}
\mathbf{B}_{19} &= \begin{matrix} -(x_6 - y_6) \mathbf{a}_1 - (x_6 + y_6) \mathbf{a}_2 - \\ z_6 \mathbf{a}_3 \end{matrix} = -(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} - cz_6 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Te I} \\
\mathbf{B}_{20} &= \begin{matrix} (x_6 + y_6) \mathbf{a}_1 + (x_6 - y_6) \mathbf{a}_2 + \\ (z_6 + \frac{1}{2}) \mathbf{a}_3 \end{matrix} = \begin{matrix} (ax_6 + c(z_6 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + \\ c(z_6 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} \end{matrix} & (8f) & \text{Te I} \\
\mathbf{B}_{21} &= \begin{matrix} (x_7 - y_7) \mathbf{a}_1 + (x_7 + y_7) \mathbf{a}_2 + \\ z_7 \mathbf{a}_3 \end{matrix} = (ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Te II} \\
\mathbf{B}_{22} &= \begin{matrix} -(x_7 + y_7) \mathbf{a}_1 - (x_7 - y_7) \mathbf{a}_2 - \\ (z_7 - \frac{1}{2}) \mathbf{a}_3 \end{matrix} = \begin{matrix} -(ax_7 + c(z_7 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} - \\ c(z_7 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}} \end{matrix} & (8f) & \text{Te II} \\
\mathbf{B}_{23} &= \begin{matrix} -(x_7 - y_7) \mathbf{a}_1 - (x_7 + y_7) \mathbf{a}_2 - \\ z_7 \mathbf{a}_3 \end{matrix} = -(ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} - cz_7 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Te II} \\
\mathbf{B}_{24} &= \begin{matrix} (x_7 + y_7) \mathbf{a}_1 + (x_7 - y_7) \mathbf{a}_2 + \\ (z_7 + \frac{1}{2}) \mathbf{a}_3 \end{matrix} = \begin{matrix} (ax_7 + c(z_7 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + \\ c(z_7 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} \end{matrix} & (8f) & \text{Te II} \\
\mathbf{B}_{25} &= \begin{matrix} (x_8 - y_8) \mathbf{a}_1 + (x_8 + y_8) \mathbf{a}_2 + \\ z_8 \mathbf{a}_3 \end{matrix} = (ax_8 + cz_8 \cos \beta) \hat{\mathbf{x}} + by_8 \hat{\mathbf{y}} + cz_8 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Te III} \\
\mathbf{B}_{26} &= \begin{matrix} -(x_8 + y_8) \mathbf{a}_1 - (x_8 - y_8) \mathbf{a}_2 - \\ (z_8 - \frac{1}{2}) \mathbf{a}_3 \end{matrix} = \begin{matrix} -(ax_8 + c(z_8 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_8 \hat{\mathbf{y}} - \\ c(z_8 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}} \end{matrix} & (8f) & \text{Te III} \\
\mathbf{B}_{27} &= \begin{matrix} -(x_8 - y_8) \mathbf{a}_1 - (x_8 + y_8) \mathbf{a}_2 - \\ z_8 \mathbf{a}_3 \end{matrix} = -(ax_8 + cz_8 \cos \beta) \hat{\mathbf{x}} - by_8 \hat{\mathbf{y}} - cz_8 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Te III} \\
\mathbf{B}_{28} &= \begin{matrix} (x_8 + y_8) \mathbf{a}_1 + (x_8 - y_8) \mathbf{a}_2 + \\ (z_8 + \frac{1}{2}) \mathbf{a}_3 \end{matrix} = \begin{matrix} (ax_8 + c(z_8 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_8 \hat{\mathbf{y}} + \\ c(z_8 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} \end{matrix} & (8f) & \text{Te III}
\end{aligned}$$

References

- [1] B. Friede and M. Jansen, *Darstellung und Kristallstruktur von Hexacaesium-hexatelluridodigermanat(III) ($\text{Cs}_6\text{Ge}_2\text{Te}_6$)*, Z. Naturforsch. B **54**, 1095–1098 (1999), doi:10.1515/znb-1999-0819.

First cited in

N. Anderson, M. J. Mehl, H. Eckert, S. Divilov, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 5*. Submitted to Computational Materials Science (2026).