


# Xanthoconite ( $\text{Ag}_3\text{AsS}_3$ ) Structure: A3BC3\_mC56\_15\_3f\_f\_3f-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/HRK9>

[https://aflow.org/p/A3BC3\\_mC56\\_15\\_3f\\_f\\_3f-001](https://aflow.org/p/A3BC3_mC56_15_3f_f_3f-001)




<b>Prototype</b>	$\text{Ag}_3\text{AsS}_3$
<b>AFLOW prototype label</b>	A3BC3_mC56_15_3f_f_3f-001
<b>Mineral name</b>	xanthoconite
<b>ICSD</b>	36352
<b>Pearson symbol</b>	mC56
<b>Space group number</b>	15
<b>Space group symbol</b>	$C2/c$
<b>AFLOW prototype command</b>	<pre>aflow --proto=A3BC3_mC56_15_3f_f_3f-001 --params=a,b/a,c/a,\beta,x1,y1,z1,x2,y2,z2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6,x7, y7,z7</pre>

- $\text{Ag}_3\text{AsS}_3$  can also be found in the rhombohedral proustite structure. (Villars, 2018) shows phase diagrams with xanthoconite at 150°C and proustite at 350°C, but (Engel, 1968) state that “[xanthoconite] is obviously more unstable than proustite.”

## Base-centered Monoclinic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}b\hat{\mathbf{y}} \\
\mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}b\hat{\mathbf{y}} \\
\mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}
\end{aligned}$$



## Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$(x_1 - y_1) \mathbf{a}_1 + (x_1 + y_1) \mathbf{a}_2 + z_1 \mathbf{a}_3$	$(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(8f)	Ag I
$\mathbf{B}_2$	$-(x_1 + y_1) \mathbf{a}_1 - (x_1 - y_1) \mathbf{a}_2 - (z_1 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_1 + c(z_1 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} - c(z_1 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ag I
$\mathbf{B}_3$	$-(x_1 - y_1) \mathbf{a}_1 - (x_1 + y_1) \mathbf{a}_2 - z_1 \mathbf{a}_3$	$-(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} - cz_1 \sin \beta \hat{\mathbf{z}}$	(8f)	Ag I
$\mathbf{B}_4$	$(x_1 + y_1) \mathbf{a}_1 + (x_1 - y_1) \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$(ax_1 + c(z_1 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ag I
$\mathbf{B}_5$	$(x_2 - y_2) \mathbf{a}_1 + (x_2 + y_2) \mathbf{a}_2 + z_2 \mathbf{a}_3$	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(8f)	Ag II
$\mathbf{B}_6$	$-(x_2 + y_2) \mathbf{a}_1 - (x_2 - y_2) \mathbf{a}_2 - (z_2 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_2 + c(z_2 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} - c(z_2 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ag II
$\mathbf{B}_7$	$-(x_2 - y_2) \mathbf{a}_1 - (x_2 + y_2) \mathbf{a}_2 - z_2 \mathbf{a}_3$	$-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} - cz_2 \sin \beta \hat{\mathbf{z}}$	(8f)	Ag II
$\mathbf{B}_8$	$(x_2 + y_2) \mathbf{a}_1 + (x_2 - y_2) \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$(ax_2 + c(z_2 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ag II
$\mathbf{B}_9$	$(x_3 - y_3) \mathbf{a}_1 + (x_3 + y_3) \mathbf{a}_2 + z_3 \mathbf{a}_3$	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(8f)	Ag III
$\mathbf{B}_{10}$	$-(x_3 + y_3) \mathbf{a}_1 - (x_3 - y_3) \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_3 + c(z_3 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ag III
$\mathbf{B}_{11}$	$-(x_3 - y_3) \mathbf{a}_1 - (x_3 + y_3) \mathbf{a}_2 - z_3 \mathbf{a}_3$	$-(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} - cz_3 \sin \beta \hat{\mathbf{z}}$	(8f)	Ag III
$\mathbf{B}_{12}$	$(x_3 + y_3) \mathbf{a}_1 + (x_3 - y_3) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$(ax_3 + c(z_3 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	Ag III
$\mathbf{B}_{13}$	$(x_4 - y_4) \mathbf{a}_1 + (x_4 + y_4) \mathbf{a}_2 + z_4 \mathbf{a}_3$	$(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \sin \beta \hat{\mathbf{z}}$	(8f)	As I
$\mathbf{B}_{14}$	$-(x_4 + y_4) \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_4 + c(z_4 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	As I
$\mathbf{B}_{15}$	$-(x_4 - y_4) \mathbf{a}_1 - (x_4 + y_4) \mathbf{a}_2 - z_4 \mathbf{a}_3$	$-(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} - cz_4 \sin \beta \hat{\mathbf{z}}$	(8f)	As I
$\mathbf{B}_{16}$	$(x_4 + y_4) \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$(ax_4 + c(z_4 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	As I
$\mathbf{B}_{17}$	$(x_5 - y_5) \mathbf{a}_1 + (x_5 + y_5) \mathbf{a}_2 + z_5 \mathbf{a}_3$	$(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \sin \beta \hat{\mathbf{z}}$	(8f)	S I
$\mathbf{B}_{18}$	$-(x_5 + y_5) \mathbf{a}_1 - (x_5 - y_5) \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_5 + c(z_5 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	S I

<b>B<sub>19</sub></b>	=	$-(x_5 - y_5) \mathbf{a}_1 - (x_5 + y_5) \mathbf{a}_2 - z_5 \mathbf{a}_3$	=	$-(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} - cz_5 \sin \beta \hat{\mathbf{z}}$	(8f)	S I
<b>B<sub>20</sub></b>	=	$(x_5 + y_5) \mathbf{a}_1 + (x_5 - y_5) \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_5 + c(z_5 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	S I
<b>B<sub>21</sub></b>	=	$(x_6 - y_6) \mathbf{a}_1 + (x_6 + y_6) \mathbf{a}_2 + z_6 \mathbf{a}_3$	=	$(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \sin \beta \hat{\mathbf{z}}$	(8f)	S II
<b>B<sub>22</sub></b>	=	$-(x_6 + y_6) \mathbf{a}_1 - (x_6 - y_6) \mathbf{a}_2 - (z_6 - \frac{1}{2}) \mathbf{a}_3$	=	$-(ax_6 + c(z_6 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} - c(z_6 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	S II
<b>B<sub>23</sub></b>	=	$-(x_6 - y_6) \mathbf{a}_1 - (x_6 + y_6) \mathbf{a}_2 - z_6 \mathbf{a}_3$	=	$-(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} - cz_6 \sin \beta \hat{\mathbf{z}}$	(8f)	S II
<b>B<sub>24</sub></b>	=	$(x_6 + y_6) \mathbf{a}_1 + (x_6 - y_6) \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_6 + c(z_6 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	S II
<b>B<sub>25</sub></b>	=	$(x_7 - y_7) \mathbf{a}_1 + (x_7 + y_7) \mathbf{a}_2 + z_7 \mathbf{a}_3$	=	$(ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \sin \beta \hat{\mathbf{z}}$	(8f)	S III
<b>B<sub>26</sub></b>	=	$-(x_7 + y_7) \mathbf{a}_1 - (x_7 - y_7) \mathbf{a}_2 - (z_7 - \frac{1}{2}) \mathbf{a}_3$	=	$-(ax_7 + c(z_7 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} - c(z_7 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	S III
<b>B<sub>27</sub></b>	=	$-(x_7 - y_7) \mathbf{a}_1 - (x_7 + y_7) \mathbf{a}_2 - z_7 \mathbf{a}_3$	=	$-(ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} - cz_7 \sin \beta \hat{\mathbf{z}}$	(8f)	S III
<b>B<sub>28</sub></b>	=	$(x_7 + y_7) \mathbf{a}_1 + (x_7 - y_7) \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_7 + c(z_7 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	S III

## References

- [1] P. Engel and W. Nowacki, *Die Kristallstruktur von Xanthokon*,  $Ag_3AsS_3$ , Acta Crystallogr. Sect. B **24**, 77–81 (1968), doi:10.1107/S056774086800172X.
- [2] P. Villars, H. Okamoto, and K. Cenzual, eds., *ASM Alloy Phase Diagram Database* (ASM International, 2018), chap. 1988 Schmid Fetzer R. (Silver-Arsenic-Sulfur). Copyright ©2006-2018 ASM International.

## Found in

- [1] R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).