


Ti₅Ga₄ Structure: A4B5_hP18_193_bg_dg-001

This structure originally had the label **A4B5_hP18_193.bg_dg**. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://afLOW.org/p/443S>

https://afLOW.org/p/A4B5_hP18_193.bg_dg-001



Prototype	Ga ₄ Ti ₅
AFLOW prototype label	A4B5_hP18_193.bg_dg-001
ICSD	103997
Pearson symbol	hP18
Space group number	193
Space group symbol	<i>P6₃/mcm</i>
AFLOW prototype command	<code>afLOW --proto=A4B5_hP18_193.bg_dg-001 --params=a, c/a, x₃, x₄</code>


Other compounds with this structure

Th₅Sn₄, Zr₅Al₄, Zr₅Ga₄, Hf₅Sn₄, Ba₃TlTe₅, NbIrO, Ce₃TiSb₅, Ce₃TiBi₅

- This is the D_{8h} structure with the addition of two atoms on the (2b) site.

Hexagonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	0	$=$	0	(2b)	Ga I
\mathbf{B}_2	$\frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}c \hat{\mathbf{z}}$	(2b)	Ga I
\mathbf{B}_3	$\frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}}$	(4d)	Ti I
\mathbf{B}_4	$\frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(4d)	Ti I
\mathbf{B}_5	$\frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}}$	(4d)	Ti I
\mathbf{B}_6	$\frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(4d)	Ti I
\mathbf{B}_7	$x_3 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}ax_3 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6g)	Ga II
\mathbf{B}_8	$x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}ax_3 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6g)	Ga II
\mathbf{B}_9	$-x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-ax_3 \hat{\mathbf{x}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6g)	Ga II
\mathbf{B}_{10}	$-x_3 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}ax_3 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6g)	Ga II
\mathbf{B}_{11}	$-x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}ax_3 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6g)	Ga II
\mathbf{B}_{12}	$x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$ax_3 \hat{\mathbf{x}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6g)	Ga II
\mathbf{B}_{13}	$x_4 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}ax_4 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6g)	Ti II
\mathbf{B}_{14}	$x_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}ax_4 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6g)	Ti II
\mathbf{B}_{15}	$-x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-ax_4 \hat{\mathbf{x}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6g)	Ti II
\mathbf{B}_{16}	$-x_4 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}ax_4 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6g)	Ti II
\mathbf{B}_{17}	$-x_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}ax_4 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6g)	Ti II
\mathbf{B}_{18}	$x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$ax_4 \hat{\mathbf{x}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6g)	Ti II

References

- [1] K. Schubert, H. G. Meissner, M. Pötzschke, W. Rossteutscher, and E. Stolz, *Einige Strukturdaten metallischer Phasen (7)*, *Naturwissenschaften* **49**, 57 (1962), doi:10.1007/BF00595382.

Found in

- [1] P. Villars, *Ti5Ga4 Crystal Structure* (2016). PAULING FILE in: *Inorganic Solid Phases*, SpringerMaterials (online database), Springer, Heidelberg (ed.) SpringerMaterials.