


B₄SrO₇ Structure: A4B7C_oP24_31_2b_a3b_a-001

This structure originally had the label A4B7C_oP24_31_2b_a3b_a. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/p/DLX0>

https://aflow.org/p/A4B7C_oP24_31_2b_a3b_a-001




Prototype	B ₄ O ₇ Sr
AFLOW prototype label	A4B7C_oP24_31_2b_a3b_a-001
ICSD	27404
Pearson symbol	oP24
Space group number	31
Space group symbol	<i>Pmn</i> 2 ₁
AFLOW prototype command	aflow --proto=A4B7C_oP24_31_2b_a3b_a-001 --params=a, b/a, c/a, y ₁ , z ₁ , y ₂ , z ₂ , x ₃ , y ₃ , z ₃ , x ₄ , y ₄ , z ₄ , x ₅ , y ₅ , z ₅ , x ₆ , y ₆ , z ₆ , x ₇ , y ₇ , z ₇

- Clinobarylite, BaBe₂Si₂O₇, is a quaternary form of this structure.
- Space group *Pmn*2₁ #31 allows an arbitrary choice of the zero of the *z*-axis. Here it is chosen so that *z*₁ = 0 for the strontium atom.

Simple Orthorhombic primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= a \hat{x} \\ \mathbf{a}_2 &= b \hat{y} \\ \mathbf{a}_3 &= c \hat{z} \end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	$= y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	$=$	$by_1 \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(2a)	O I
\mathbf{B}_2	$= \frac{1}{2} \mathbf{a}_1 - y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(2a)	O I
\mathbf{B}_3	$= y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$by_2 \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(2a)	Sr I
\mathbf{B}_4	$= \frac{1}{2} \mathbf{a}_1 - y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(2a)	Sr I
\mathbf{B}_5	$= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$ax_3 \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(4b)	B I
\mathbf{B}_6	$= -(x_3 - \frac{1}{2}) \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_3 - \frac{1}{2}) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	B I
\mathbf{B}_7	$= (x_3 + \frac{1}{2}) \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a(x_3 + \frac{1}{2}) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	B I
\mathbf{B}_8	$= -x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$-ax_3 \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(4b)	B I
\mathbf{B}_9	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$ax_4 \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(4b)	B II
\mathbf{B}_{10}	$= -(x_4 - \frac{1}{2}) \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_4 - \frac{1}{2}) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	B II
\mathbf{B}_{11}	$= (x_4 + \frac{1}{2}) \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a(x_4 + \frac{1}{2}) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	B II
\mathbf{B}_{12}	$= -x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$-ax_4 \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(4b)	B II
\mathbf{B}_{13}	$= x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$ax_5 \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(4b)	O II
\mathbf{B}_{14}	$= -(x_5 - \frac{1}{2}) \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_5 - \frac{1}{2}) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	O II
\mathbf{B}_{15}	$= (x_5 + \frac{1}{2}) \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a(x_5 + \frac{1}{2}) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	O II
\mathbf{B}_{16}	$= -x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$-ax_5 \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(4b)	O II
\mathbf{B}_{17}	$= x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	$=$	$ax_6 \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(4b)	O III
\mathbf{B}_{18}	$= -(x_6 - \frac{1}{2}) \mathbf{a}_1 - y_6 \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_6 - \frac{1}{2}) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	O III
\mathbf{B}_{19}	$= (x_6 + \frac{1}{2}) \mathbf{a}_1 - y_6 \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a(x_6 + \frac{1}{2}) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	O III
\mathbf{B}_{20}	$= -x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	$=$	$-ax_6 \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(4b)	O III
\mathbf{B}_{21}	$= x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	$=$	$ax_7 \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \hat{\mathbf{z}}$	(4b)	O IV
\mathbf{B}_{22}	$= -(x_7 - \frac{1}{2}) \mathbf{a}_1 - y_7 \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_7 - \frac{1}{2}) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	O IV
\mathbf{B}_{23}	$= (x_7 + \frac{1}{2}) \mathbf{a}_1 - y_7 \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a(x_7 + \frac{1}{2}) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \hat{\mathbf{z}}$	(4b)	O IV
\mathbf{B}_{24}	$= -x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	$=$	$-ax_7 \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \hat{\mathbf{z}}$	(4b)	O IV

References

- [1] J. Krogh-Moe, *The Crystal Structure of Strontium Diborate, SrO·2B₂O₃*, Acta Chem. Scand. **18**, 2055–2060 (1964), doi:10.3891/acta.chem.scand.18-2055.