

SrSn₄ Structure:


A4B_oC20_63_acf_c-001

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/9ZDH>

https://aflow.org/prototype-encyclopedia/A4B_oC20_63_acf_c-001



Prototype	Sn ₄ Sr
AFLOW prototype label	A4B_oC20_63_acf_c-001
ICSD	281669
CCDC	1722117
Pearson symbol	oC20
Space group number	63
Space group symbol	<i>Cmcm</i>

AFLOW prototype command `aflow --proto=A4B_oC20_63_acf_c-001`
 `--params=a, b/a, c/a, y2, y3, y4, z4`


- The equilibrium phase diagram for the Sn-Sr system has been mapped by (Palenzona, 384):

Formula	Structure
Sr	fcc (<i>A1</i>)
Sr ₂ Sn	Cotunnite, PbCl ₂ (<i>C23</i>)
Sr ₅ Sn ₃	Cr ₅ B ₃ (<i>D8_I</i>)
SrSn	CrB (<i>B33</i>)
Sr ₃ Sn ₅	Pd ₅ Pu ₃
SrSn ₃	SrSn ₃
SrSn ₄	SrSn ₄ (this structure)
Sn	diamond (<i>A4</i>) or β -Sn (<i>A5</i>)

- This structure is superconducting below 4.8K

Base-centered Orthorhombic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= 0$	$=$	0	(4a)	Sn I
$\mathbf{B}_2$	$= \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}c \hat{\mathbf{z}}$	(4a)	Sn I
$\mathbf{B}_3$	$= -y_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$by_2 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(4c)	Sn II
$\mathbf{B}_4$	$= y_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-by_2 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(4c)	Sn II
$\mathbf{B}_5$	$= -y_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$by_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(4c)	Sr I
$\mathbf{B}_6$	$= y_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-by_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(4c)	Sr I
$\mathbf{B}_7$	$= -y_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(8f)	Sn III
$\mathbf{B}_8$	$= y_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	Sn III
$\mathbf{B}_9$	$= -y_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$=$	$by_4 \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	Sn III
$\mathbf{B}_{10}$	$= y_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-by_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(8f)	Sn III

References

- [1] S. Hoffmann and T. F. Fässler, *SrSn₄: A Superconducting Stannide with Localized and Delocalized Bond Character*, Inorg. Chem. **42**, 8748–8754 (2003), doi:10.1021/ic0302128.
- [2] A. Palenzona and M. Pani, *The phase diagram of the Sr-Sn system*, J. Alloys Compd. **384**, 227–230 (2004), doi:10.1016/j.jallcom.2004.04.097.

First cited in

N. Anderson, M. J. Mehl, H. Eckert, S. Divilov, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 5*. Submitted to Computational Materials Science (2026).