


# Y<sub>2</sub>SiO<sub>5</sub> (RE<sub>2</sub>SiO<sub>5</sub> X2) Structure: A5BC2\_mC64\_15\_5f\_f\_2f-001

This structure originally had the label A5BC2\_mC64\_15\_5f\_f\_2f. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/p/G8V5>

[https://aflow.org/p/A5BC2\\_mC64\\_15\\_5f\\_f\\_2f-001](https://aflow.org/p/A5BC2_mC64_15_5f_f_2f-001)



Prototype	O <sub>5</sub> SiY <sub>2</sub>
AFLOW prototype label	A5BC2_mC64_15_5f_f_2f-001
ICSD	27003
Pearson symbol	mC64
Space group number	15
Space group symbol	C2/c
AFLOW prototype command	<pre>aflow --proto=A5BC2_mC64_15_5f_f_2f-001       --params=a, b/a, c/a, β, x<sub>1</sub>, y<sub>1</sub>, z<sub>1</sub>, x<sub>2</sub>, y<sub>2</sub>, z<sub>2</sub>, x<sub>3</sub>, y<sub>3</sub>, z<sub>3</sub>, x<sub>4</sub>, y<sub>4</sub>, z<sub>4</sub>, x<sub>5</sub>, y<sub>5</sub>, z<sub>5</sub>, x<sub>6</sub>, y<sub>6</sub>, z<sub>6</sub>, x<sub>7</sub>,       y<sub>7</sub>, z<sub>7</sub>, x<sub>8</sub>, y<sub>8</sub>, z<sub>8</sub></pre>


## Other compounds with this structure

Dy<sub>2</sub>SiO<sub>5</sub>, Er<sub>2</sub>SiO<sub>5</sub>, Ho<sub>2</sub>SiO<sub>5</sub>, Lu<sub>2</sub>SiO<sub>5</sub>, Tb<sub>2</sub>SiO<sub>5</sub>, Tm<sub>2</sub>SiO<sub>5</sub>, Yb<sub>2</sub>SiO<sub>5</sub>

- Compounds of the form RE<sub>2</sub>SiO<sub>5</sub> (RE = Rare Earth and related elements) crystallize in one of two forms (Wang, 2001 and Tian, 2016):
- X1, space group *P*2<sub>1</sub>/*c* #14, for rare earths between lanthanum and gadolinium, and X2, this structure, for the later rare earths. Dysprosium, yttrium and ytterbium compounds exist in both structures.
- This is the high temperature phase of Y<sub>2</sub>SiO<sub>5</sub>. Below 1190°C it transforms into the X1 phase.
- The ICSD entry is from (Michel, 1967).

## Base-centered Monoclinic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}\end{aligned}$$



## Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$(x_1 - y_1) \mathbf{a}_1 + (x_1 + y_1) \mathbf{a}_2 + z_1 \mathbf{a}_3$	=	$(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(8f)	O I
$\mathbf{B}_2$	$-(x_1 + y_1) \mathbf{a}_1 - (x_1 - y_1) \mathbf{a}_2 - (z_1 - \frac{1}{2}) \mathbf{a}_3$	=	$-(ax_1 + c(z_1 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} - c(z_1 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O I
$\mathbf{B}_3$	$-(x_1 - y_1) \mathbf{a}_1 - (x_1 + y_1) \mathbf{a}_2 - z_1 \mathbf{a}_3$	=	$-(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} - cz_1 \sin \beta \hat{\mathbf{z}}$	(8f)	O I
$\mathbf{B}_4$	$(x_1 + y_1) \mathbf{a}_1 + (x_1 - y_1) \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_1 + c(z_1 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O I
$\mathbf{B}_5$	$(x_2 - y_2) \mathbf{a}_1 + (x_2 + y_2) \mathbf{a}_2 + z_2 \mathbf{a}_3$	=	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(8f)	O II
$\mathbf{B}_6$	$-(x_2 + y_2) \mathbf{a}_1 - (x_2 - y_2) \mathbf{a}_2 - (z_2 - \frac{1}{2}) \mathbf{a}_3$	=	$-(ax_2 + c(z_2 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} - c(z_2 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O II
$\mathbf{B}_7$	$-(x_2 - y_2) \mathbf{a}_1 - (x_2 + y_2) \mathbf{a}_2 - z_2 \mathbf{a}_3$	=	$-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} - cz_2 \sin \beta \hat{\mathbf{z}}$	(8f)	O II
$\mathbf{B}_8$	$(x_2 + y_2) \mathbf{a}_1 + (x_2 - y_2) \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_2 + c(z_2 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O II
$\mathbf{B}_9$	$(x_3 - y_3) \mathbf{a}_1 + (x_3 + y_3) \mathbf{a}_2 + z_3 \mathbf{a}_3$	=	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(8f)	O III
$\mathbf{B}_{10}$	$-(x_3 + y_3) \mathbf{a}_1 - (x_3 - y_3) \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	=	$-(ax_3 + c(z_3 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O III
$\mathbf{B}_{11}$	$-(x_3 - y_3) \mathbf{a}_1 - (x_3 + y_3) \mathbf{a}_2 - z_3 \mathbf{a}_3$	=	$-(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} - cz_3 \sin \beta \hat{\mathbf{z}}$	(8f)	O III
$\mathbf{B}_{12}$	$(x_3 + y_3) \mathbf{a}_1 + (x_3 - y_3) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_3 + c(z_3 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O III
$\mathbf{B}_{13}$	$(x_4 - y_4) \mathbf{a}_1 + (x_4 + y_4) \mathbf{a}_2 + z_4 \mathbf{a}_3$	=	$(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \sin \beta \hat{\mathbf{z}}$	(8f)	O IV
$\mathbf{B}_{14}$	$-(x_4 + y_4) \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	=	$-(ax_4 + c(z_4 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O IV
$\mathbf{B}_{15}$	$-(x_4 - y_4) \mathbf{a}_1 - (x_4 + y_4) \mathbf{a}_2 - z_4 \mathbf{a}_3$	=	$-(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} - cz_4 \sin \beta \hat{\mathbf{z}}$	(8f)	O IV
$\mathbf{B}_{16}$	$(x_4 + y_4) \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_4 + c(z_4 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O IV
$\mathbf{B}_{17}$	$(x_5 - y_5) \mathbf{a}_1 + (x_5 + y_5) \mathbf{a}_2 + z_5 \mathbf{a}_3$	=	$(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \sin \beta \hat{\mathbf{z}}$	(8f)	O V
$\mathbf{B}_{18}$	$-(x_5 + y_5) \mathbf{a}_1 - (x_5 - y_5) \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	=	$-(ax_5 + c(z_5 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}}$	(8f)	O V

$$\begin{aligned}
\mathbf{B}_{19} &= -(x_5 - y_5) \mathbf{a}_1 - (x_5 + y_5) \mathbf{a}_2 - z_5 \mathbf{a}_3 = -(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} - cz_5 \sin \beta \hat{\mathbf{z}} & (8f) & \text{O V} \\
\mathbf{B}_{20} &= (x_5 + y_5) \mathbf{a}_1 + (x_5 - y_5) \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3 = (ax_5 + c(z_5 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} & (8f) & \text{O V} \\
\mathbf{B}_{21} &= (x_6 - y_6) \mathbf{a}_1 + (x_6 + y_6) \mathbf{a}_2 + z_6 \mathbf{a}_3 = (ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Si I} \\
\mathbf{B}_{22} &= -(x_6 + y_6) \mathbf{a}_1 - (x_6 - y_6) \mathbf{a}_2 - (z_6 - \frac{1}{2}) \mathbf{a}_3 = -(ax_6 + c(z_6 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} - c(z_6 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}} & (8f) & \text{Si I} \\
\mathbf{B}_{23} &= -(x_6 - y_6) \mathbf{a}_1 - (x_6 + y_6) \mathbf{a}_2 - z_6 \mathbf{a}_3 = -(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} - cz_6 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Si I} \\
\mathbf{B}_{24} &= (x_6 + y_6) \mathbf{a}_1 + (x_6 - y_6) \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3 = (ax_6 + c(z_6 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} & (8f) & \text{Si I} \\
\mathbf{B}_{25} &= (x_7 - y_7) \mathbf{a}_1 + (x_7 + y_7) \mathbf{a}_2 + z_7 \mathbf{a}_3 = (ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y I} \\
\mathbf{B}_{26} &= -(x_7 + y_7) \mathbf{a}_1 - (x_7 - y_7) \mathbf{a}_2 - (z_7 - \frac{1}{2}) \mathbf{a}_3 = -(ax_7 + c(z_7 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} - c(z_7 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y I} \\
\mathbf{B}_{27} &= -(x_7 - y_7) \mathbf{a}_1 - (x_7 + y_7) \mathbf{a}_2 - z_7 \mathbf{a}_3 = -(ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} - cz_7 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y I} \\
\mathbf{B}_{28} &= (x_7 + y_7) \mathbf{a}_1 + (x_7 - y_7) \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3 = (ax_7 + c(z_7 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y I} \\
\mathbf{B}_{29} &= (x_8 - y_8) \mathbf{a}_1 + (x_8 + y_8) \mathbf{a}_2 + z_8 \mathbf{a}_3 = (ax_8 + cz_8 \cos \beta) \hat{\mathbf{x}} + by_8 \hat{\mathbf{y}} + cz_8 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y II} \\
\mathbf{B}_{30} &= -(x_8 + y_8) \mathbf{a}_1 - (x_8 - y_8) \mathbf{a}_2 - (z_8 - \frac{1}{2}) \mathbf{a}_3 = -(ax_8 + c(z_8 - \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} + by_8 \hat{\mathbf{y}} - c(z_8 - \frac{1}{2}) \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y II} \\
\mathbf{B}_{31} &= -(x_8 - y_8) \mathbf{a}_1 - (x_8 + y_8) \mathbf{a}_2 - z_8 \mathbf{a}_3 = -(ax_8 + cz_8 \cos \beta) \hat{\mathbf{x}} - by_8 \hat{\mathbf{y}} - cz_8 \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y II} \\
\mathbf{B}_{32} &= (x_8 + y_8) \mathbf{a}_1 + (x_8 - y_8) \mathbf{a}_2 + (z_8 + \frac{1}{2}) \mathbf{a}_3 = (ax_8 + c(z_8 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_8 \hat{\mathbf{y}} + c(z_8 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} & (8f) & \text{Y II}
\end{aligned}$$

## References

- [1] G. V. Anan'eva, A. M. Korovkin, T. I. Merkulyaeva, A. M. Morozova, M. V. Petrov, I. R. Savinova, V. R. Startsev, and P. P. Feofilov, *Growth of lanthanide oxyorthosilicate single crystals, and their structural and optical characteristics*, Inorg. Mater. **17**, 754–758 (1981). Translated from *Neorganicheskie Materialy*.
- [2] J. Wang, S. Tian, G. Li, F. Liao, and X. Jing, *Preparation and X-ray characterization of low-temperature phases of  $R_2SiO_5$  ( $R = \text{rare earth elements}$ )*, Mater. Res. Bull. **36**, 1855–1861 (2001), doi:10.1016/S0025-5408(01)00664-X.
- [3] Z. Tian, L. Zheng, J. Wang, P. Wan, J. Li, and J. Wang, *Theoretical and experimental determination of the major thermo-mechanical properties of  $RE_2SiO_5$  ( $RE = Tb, Dy, Ho, Er, Tm, Yb, Lu, \text{ and } Y$ ) for environmental and thermal barrier coating applications*, J. Am. Ceram. Soc. **36**, 189–202 (2016), doi:10.1016/j.jeurceramsoc.2015.09.013.
- [4] C. Michel, G. Buisson, and E. F. Bertaut, *Structure de  $Y_2SiO_5$* , Compt. Rend. B: Sci. Phys. **264**, 397–399 (1967).
- [5] M. D. Dramićanin, V. Jokanović, B. Viana, E. Antic-Fidancev, M. Mitrić, and ž. Andrić, *Luminescence and structural properties of  $Gd_2SiO_5:Eu^{3+}$  nanophosphors synthesized from the hydrothermal obtained silica sol*, Journal of Alloys and Compounds **424**, 213–217 (2006), doi:10.1016/j.jallcom.2005.10.086.

## Found in

- [1] P. Villars, *Y2SiO5 (Y2[SiO4]O ht) Crystal Structure* (2016). PAULING FILE in: Inorganic Solid Phases, SpringerMaterials (online database), Springer, Heidelberg (ed.) SpringerMaterials.