


Ca₅Ga₂As₆ Structure: A6B5C2_oP26_55_g2h_a2g_h-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://afLOW.org/p/JZ3U>

https://afLOW.org/p/A6B5C2_oP26_55_g2h_a2g_h-001



Prototype	Ca ₅ Ga ₂ As ₆
AFLOW prototype label	A6B5C2_oP26_55_g2h_a2g_h-001
ICSD	27
Pearson symbol	oP26
Space group number	55
Space group symbol	<i>Pbam</i>
AFLOW prototype command	<code>afLOW --proto=A6B5C2_oP26_55_g2h_a2g_h-001</code> <code>--params=a, b/a, c/a, x₂, y₂, x₃, y₃, x₄, y₄, x₅, y₅, x₆, y₆, x₇, y₇</code>


Other compounds with this structure

Ca₅Al₂Bi₆, Ca₅Al₂Sb₆, Ca₅Ga₂Sb₆, Ca₅In₂Sb₆, Eu₅In₂Sb₆, Sr₅In₂Sb₆

- (Verdier, 1976) place the origin so that the Ca-I atoms are at the (2d) Wyckoff position. We shifted the origin to place them on the (2a) Wyckoff sites.

Simple Orthorhombic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	$= 0$	$=$	0	(2a)	Ca I
\mathbf{B}_2	$= \frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} + \frac{1}{2} b \hat{\mathbf{y}}$	(2a)	Ca I
\mathbf{B}_3	$= x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2$	$=$	$a x_2 \hat{\mathbf{x}} + b y_2 \hat{\mathbf{y}}$	(4g)	As I
\mathbf{B}_4	$= -x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2$	$=$	$-a x_2 \hat{\mathbf{x}} - b y_2 \hat{\mathbf{y}}$	(4g)	As I
\mathbf{B}_5	$= -(x_2 - \frac{1}{2}) \mathbf{a}_1 + (y_2 + \frac{1}{2}) \mathbf{a}_2$	$=$	$-a (x_2 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_2 + \frac{1}{2}) \hat{\mathbf{y}}$	(4g)	As I
\mathbf{B}_6	$= (x_2 + \frac{1}{2}) \mathbf{a}_1 - (y_2 - \frac{1}{2}) \mathbf{a}_2$	$=$	$a (x_2 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_2 - \frac{1}{2}) \hat{\mathbf{y}}$	(4g)	As I
\mathbf{B}_7	$= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2$	$=$	$a x_3 \hat{\mathbf{x}} + b y_3 \hat{\mathbf{y}}$	(4g)	Ca II
\mathbf{B}_8	$= -x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2$	$=$	$-a x_3 \hat{\mathbf{x}} - b y_3 \hat{\mathbf{y}}$	(4g)	Ca II
\mathbf{B}_9	$= -(x_3 - \frac{1}{2}) \mathbf{a}_1 + (y_3 + \frac{1}{2}) \mathbf{a}_2$	$=$	$-a (x_3 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_3 + \frac{1}{2}) \hat{\mathbf{y}}$	(4g)	Ca II
\mathbf{B}_{10}	$= (x_3 + \frac{1}{2}) \mathbf{a}_1 - (y_3 - \frac{1}{2}) \mathbf{a}_2$	$=$	$a (x_3 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_3 - \frac{1}{2}) \hat{\mathbf{y}}$	(4g)	Ca II
\mathbf{B}_{11}	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2$	$=$	$a x_4 \hat{\mathbf{x}} + b y_4 \hat{\mathbf{y}}$	(4g)	Ca III
\mathbf{B}_{12}	$= -x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2$	$=$	$-a x_4 \hat{\mathbf{x}} - b y_4 \hat{\mathbf{y}}$	(4g)	Ca III
\mathbf{B}_{13}	$= -(x_4 - \frac{1}{2}) \mathbf{a}_1 + (y_4 + \frac{1}{2}) \mathbf{a}_2$	$=$	$-a (x_4 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_4 + \frac{1}{2}) \hat{\mathbf{y}}$	(4g)	Ca III
\mathbf{B}_{14}	$= (x_4 + \frac{1}{2}) \mathbf{a}_1 - (y_4 - \frac{1}{2}) \mathbf{a}_2$	$=$	$a (x_4 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_4 - \frac{1}{2}) \hat{\mathbf{y}}$	(4g)	Ca III
\mathbf{B}_{15}	$= x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a x_5 \hat{\mathbf{x}} + b y_5 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As II
\mathbf{B}_{16}	$= -x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-a x_5 \hat{\mathbf{x}} - b y_5 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As II
\mathbf{B}_{17}	$= -(x_5 - \frac{1}{2}) \mathbf{a}_1 + (y_5 + \frac{1}{2}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-a (x_5 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_5 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As II
\mathbf{B}_{18}	$= (x_5 + \frac{1}{2}) \mathbf{a}_1 - (y_5 - \frac{1}{2}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a (x_5 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_5 - \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As II
\mathbf{B}_{19}	$= x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a x_6 \hat{\mathbf{x}} + b y_6 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As III
\mathbf{B}_{20}	$= -x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-a x_6 \hat{\mathbf{x}} - b y_6 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As III
\mathbf{B}_{21}	$= -(x_6 - \frac{1}{2}) \mathbf{a}_1 + (y_6 + \frac{1}{2}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-a (x_6 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_6 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As III
\mathbf{B}_{22}	$= (x_6 + \frac{1}{2}) \mathbf{a}_1 - (y_6 - \frac{1}{2}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a (x_6 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_6 - \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	As III
\mathbf{B}_{23}	$= x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a x_7 \hat{\mathbf{x}} + b y_7 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	Ga I
\mathbf{B}_{24}	$= -x_7 \mathbf{a}_1 - y_7 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-a x_7 \hat{\mathbf{x}} - b y_7 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	Ga I
\mathbf{B}_{25}	$= -(x_7 - \frac{1}{2}) \mathbf{a}_1 + (y_7 + \frac{1}{2}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-a (x_7 - \frac{1}{2}) \hat{\mathbf{x}} + b (y_7 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	Ga I
\mathbf{B}_{26}	$= (x_7 + \frac{1}{2}) \mathbf{a}_1 - (y_7 - \frac{1}{2}) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a (x_7 + \frac{1}{2}) \hat{\mathbf{x}} - b (y_7 - \frac{1}{2}) \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$	(4h)	Ga I

References

- [1] P. Verdier, P. L'Haridon, M. Maunaye, and Y. Laurent, *Etude Structural de $Ca_5Ga_2As_6$* , Acta Crystallogr. Sect. B **32**, 726–728 (1976), doi:10.1107/S0567740876003889.