


Mg₆MnO₈ Structure: A6BC8_cF60_225_d_a_ce-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/4YGB>

https://aflow.org/p/A6BC8_cF60_225_d_a_ce-001



Prototype	Mg ₆ MnO ₈
AFLOW prototype label	A6BC8_cF60_225_d_a_ce-001
ICSD	24710
Pearson symbol	cF60
Space group number	225
Space group symbol	$Fm\bar{3}m$
AFLOW prototype command	<code>aflow --proto=A6BC8_cF60_225_d_a_ce-001 --params=a, x₄</code>


Other compounds with this structure

Na₆CdCl₈, Na₆FeCl₈, Na₆MgCl₈, Na₆MnCl₈

- This can be seen as a distortion of the rock salt (*B1*) structure with four atoms removed. Adding atoms to the (4b) site and setting $x_4 = 1/4$ places all of the atoms on the sites of the rock salt crystal.

Face-centered Cubic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}a\hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}}\end{aligned}$$



Basis vectors

	Lattice coordinates	=	Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	0	=	0	(4a)	Mn I
\mathbf{B}_2	$\frac{1}{4}\mathbf{a}_1 + \frac{1}{4}\mathbf{a}_2 + \frac{1}{4}\mathbf{a}_3$	=	$\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{y}} + \frac{1}{4}a\hat{\mathbf{z}}$	(8c)	O I
\mathbf{B}_3	$\frac{3}{4}\mathbf{a}_1 + \frac{3}{4}\mathbf{a}_2 + \frac{3}{4}\mathbf{a}_3$	=	$\frac{3}{4}a\hat{\mathbf{x}} + \frac{3}{4}a\hat{\mathbf{y}} + \frac{3}{4}a\hat{\mathbf{z}}$	(8c)	O I
\mathbf{B}_4	$\frac{1}{2}\mathbf{a}_1$	=	$\frac{1}{4}a\hat{\mathbf{y}} + \frac{1}{4}a\hat{\mathbf{z}}$	(24d)	Mg I
\mathbf{B}_5	$\frac{1}{2}\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{y}} + \frac{1}{4}a\hat{\mathbf{z}}$	(24d)	Mg I
\mathbf{B}_6	$\frac{1}{2}\mathbf{a}_2$	=	$\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{z}}$	(24d)	Mg I
\mathbf{B}_7	$\frac{1}{2}\mathbf{a}_1 + \frac{1}{2}\mathbf{a}_3$	=	$\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{4}a\hat{\mathbf{z}}$	(24d)	Mg I
\mathbf{B}_8	$\frac{1}{2}\mathbf{a}_3$	=	$\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{y}}$	(24d)	Mg I
\mathbf{B}_9	$\frac{1}{2}\mathbf{a}_1 + \frac{1}{2}\mathbf{a}_2$	=	$\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{y}} + \frac{1}{2}a\hat{\mathbf{z}}$	(24d)	Mg I
\mathbf{B}_{10}	$-x_4\mathbf{a}_1 + x_4\mathbf{a}_2 + x_4\mathbf{a}_3$	=	$ax_4\hat{\mathbf{x}}$	(24e)	O II
\mathbf{B}_{11}	$x_4\mathbf{a}_1 - x_4\mathbf{a}_2 - x_4\mathbf{a}_3$	=	$-ax_4\hat{\mathbf{x}}$	(24e)	O II
\mathbf{B}_{12}	$x_4\mathbf{a}_1 - x_4\mathbf{a}_2 + x_4\mathbf{a}_3$	=	$ax_4\hat{\mathbf{y}}$	(24e)	O II
\mathbf{B}_{13}	$-x_4\mathbf{a}_1 + x_4\mathbf{a}_2 - x_4\mathbf{a}_3$	=	$-ax_4\hat{\mathbf{y}}$	(24e)	O II
\mathbf{B}_{14}	$x_4\mathbf{a}_1 + x_4\mathbf{a}_2 - x_4\mathbf{a}_3$	=	$ax_4\hat{\mathbf{z}}$	(24e)	O II
\mathbf{B}_{15}	$-x_4\mathbf{a}_1 - x_4\mathbf{a}_2 + x_4\mathbf{a}_3$	=	$-ax_4\hat{\mathbf{z}}$	(24e)	O II

References

- [1] J. S. Kasper and J. S. Prener, *The Crystal Structure of Mg_6MnO_8* , Acta Cryst. **7**, 246–248 (1954), doi:10.1107/S0365110X54000722.