


# Rh<sub>2</sub>Ga<sub>9</sub> Structure: A9B2\_mP22\_7\_9a\_2a-001

This structure originally had the label **A9B2\_mP22\_7\_9a\_2a**. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043

<https://aflow.org/p/2DRY>

[https://aflow.org/p/A9B2\\_mP22\\_7\\_9a\\_2a-001](https://aflow.org/p/A9B2_mP22_7_9a_2a-001)



Prototype	Ga <sub>9</sub> Rh <sub>2</sub>
AFLOW prototype label	A9B2_mP22_7_9a_2a-001
ICSD	414305
Pearson symbol	mP22
Space group number	7
Space group symbol	<i>Pc</i>
AFLOW prototype command	<code>aflow --proto=A9B2_mP22_7_9a_2a-001 --params=a, b/a, c/a, β, x<sub>1</sub>, y<sub>1</sub>, z<sub>1</sub>, x<sub>2</sub>, y<sub>2</sub>, z<sub>2</sub>, x<sub>3</sub>, y<sub>3</sub>, z<sub>3</sub>, x<sub>4</sub>, y<sub>4</sub>, z<sub>4</sub>, x<sub>5</sub>, y<sub>5</sub>, z<sub>5</sub>, x<sub>6</sub>, y<sub>6</sub>, z<sub>6</sub>, x<sub>7</sub>, y<sub>7</sub>, z<sub>7</sub>, x<sub>8</sub>, y<sub>8</sub>, z<sub>8</sub>, x<sub>9</sub>, y<sub>9</sub>, z<sub>9</sub>, x<sub>10</sub>, y<sub>10</sub>, z<sub>10</sub>, x<sub>11</sub>, y<sub>11</sub>, z<sub>11</sub></code>

---

## Other compounds with this structure


Ir<sub>2</sub>Ga<sub>9</sub>

---

## Simple Monoclinic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \hat{x} \\
\mathbf{a}_2 &= \hat{y} \\
\mathbf{a}_3 &= c \cos \beta \hat{x} + c \sin \beta \hat{z}
\end{aligned}$$

a1  
a2  
a3



## Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	=	$(ax_1 + cz_1 \cos \beta) \hat{x} + by_1 \hat{y} + cz_1 \sin \beta \hat{z}$	(2a)	Ga I
$\mathbf{B}_2$	$x_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_1 + c(z_1 + \frac{1}{2}) \cos \beta) \hat{x} - by_1 \hat{y} + c(z_1 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga I
$\mathbf{B}_3$	$x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	=	$(ax_2 + cz_2 \cos \beta) \hat{x} + by_2 \hat{y} + cz_2 \sin \beta \hat{z}$	(2a)	Ga II
$\mathbf{B}_4$	$x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_2 + c(z_2 + \frac{1}{2}) \cos \beta) \hat{x} - by_2 \hat{y} + c(z_2 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga II
$\mathbf{B}_5$	$x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	=	$(ax_3 + cz_3 \cos \beta) \hat{x} + by_3 \hat{y} + cz_3 \sin \beta \hat{z}$	(2a)	Ga III
$\mathbf{B}_6$	$x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_3 + c(z_3 + \frac{1}{2}) \cos \beta) \hat{x} - by_3 \hat{y} + c(z_3 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga III
$\mathbf{B}_7$	$x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	=	$(ax_4 + cz_4 \cos \beta) \hat{x} + by_4 \hat{y} + cz_4 \sin \beta \hat{z}$	(2a)	Ga IV
$\mathbf{B}_8$	$x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_4 + c(z_4 + \frac{1}{2}) \cos \beta) \hat{x} - by_4 \hat{y} + c(z_4 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga IV
$\mathbf{B}_9$	$x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	=	$(ax_5 + cz_5 \cos \beta) \hat{x} + by_5 \hat{y} + cz_5 \sin \beta \hat{z}$	(2a)	Ga V
$\mathbf{B}_{10}$	$x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_5 + c(z_5 + \frac{1}{2}) \cos \beta) \hat{x} - by_5 \hat{y} + c(z_5 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga V
$\mathbf{B}_{11}$	$x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	=	$(ax_6 + cz_6 \cos \beta) \hat{x} + by_6 \hat{y} + cz_6 \sin \beta \hat{z}$	(2a)	Ga VI
$\mathbf{B}_{12}$	$x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_6 + c(z_6 + \frac{1}{2}) \cos \beta) \hat{x} - by_6 \hat{y} + c(z_6 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga VI
$\mathbf{B}_{13}$	$x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	=	$(ax_7 + cz_7 \cos \beta) \hat{x} + by_7 \hat{y} + cz_7 \sin \beta \hat{z}$	(2a)	Ga VII
$\mathbf{B}_{14}$	$x_7 \mathbf{a}_1 - y_7 \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_7 + c(z_7 + \frac{1}{2}) \cos \beta) \hat{x} - by_7 \hat{y} + c(z_7 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga VII
$\mathbf{B}_{15}$	$x_8 \mathbf{a}_1 + y_8 \mathbf{a}_2 + z_8 \mathbf{a}_3$	=	$(ax_8 + cz_8 \cos \beta) \hat{x} + by_8 \hat{y} + cz_8 \sin \beta \hat{z}$	(2a)	Ga VIII
$\mathbf{B}_{16}$	$x_8 \mathbf{a}_1 - y_8 \mathbf{a}_2 + (z_8 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_8 + c(z_8 + \frac{1}{2}) \cos \beta) \hat{x} - by_8 \hat{y} + c(z_8 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga VIII
$\mathbf{B}_{17}$	$x_9 \mathbf{a}_1 + y_9 \mathbf{a}_2 + z_9 \mathbf{a}_3$	=	$(ax_9 + cz_9 \cos \beta) \hat{x} + by_9 \hat{y} + cz_9 \sin \beta \hat{z}$	(2a)	Ga IX
$\mathbf{B}_{18}$	$x_9 \mathbf{a}_1 - y_9 \mathbf{a}_2 + (z_9 + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_9 + c(z_9 + \frac{1}{2}) \cos \beta) \hat{x} - by_9 \hat{y} + c(z_9 + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Ga IX
$\mathbf{B}_{19}$	$x_{10} \mathbf{a}_1 + y_{10} \mathbf{a}_2 + z_{10} \mathbf{a}_3$	=	$(ax_{10} + cz_{10} \cos \beta) \hat{x} + by_{10} \hat{y} + cz_{10} \sin \beta \hat{z}$	(2a)	Rh I
$\mathbf{B}_{20}$	$x_{10} \mathbf{a}_1 - y_{10} \mathbf{a}_2 + (z_{10} + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_{10} + c(z_{10} + \frac{1}{2}) \cos \beta) \hat{x} - by_{10} \hat{y} + c(z_{10} + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Rh I
$\mathbf{B}_{21}$	$x_{11} \mathbf{a}_1 + y_{11} \mathbf{a}_2 + z_{11} \mathbf{a}_3$	=	$(ax_{11} + cz_{11} \cos \beta) \hat{x} + by_{11} \hat{y} + cz_{11} \sin \beta \hat{z}$	(2a)	Rh II
$\mathbf{B}_{22}$	$x_{11} \mathbf{a}_1 - y_{11} \mathbf{a}_2 + (z_{11} + \frac{1}{2}) \mathbf{a}_3$	=	$(ax_{11} + c(z_{11} + \frac{1}{2}) \cos \beta) \hat{x} - by_{11} \hat{y} + c(z_{11} + \frac{1}{2}) \sin \beta \hat{z}$	(2a)	Rh II

## References

- [1] M. Boström, H. Rosner, Y. Prots, U. Burkhardt, and Y. Grin, *The  $Co_2Al_9$  Structure Type Revisited*, *Z. Anorganische und Allgemeine Chemie* **631**, 534–541 (2005), doi:10.1002/zaac.200400418.

## Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.