





# Miargyrite ( $\text{AgSbS}_2$ ) Structure: AB<sub>2</sub>C\_mC32\_15\_ae\_2f\_f-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/YUVG>

[https://aflow.org/p/AB2C\\_mC32\\_15\\_ae\\_2f\\_f-001](https://aflow.org/p/AB2C_mC32_15_ae_2f_f-001)

● Ag  
● S  
● Sb



**Prototype**  $\text{AgS}_2\text{Sb}$

**AFLOW prototype label** AB<sub>2</sub>C\_mC32\_15\_ae\_2f\_f-001

**Mineral name** miargyrite

**ICSD** 94647

**Pearson symbol** mC32

**Space group number** 15


**Space group symbol**  $C2/c$

**AFLOW prototype command** `aflow --proto=AB2C_mC32_15_ae_2f_f-001 --params=a, b/a, c/a,  $\beta$ ,  $y_2$ ,  $x_3$ ,  $y_3$ ,  $z_3$ ,  $x_4$ ,  $y_4$ ,  $z_4$ ,  $x_5$ ,  $y_5$ ,  $z_5$`

- We shifted the origin of the structure described by (Effenberger, 2002) so that a silver atom is at the origin, the Wyckoff (4a) site, rather than at (0 1/2 1/2), Wyckoff (4b).

## Base-centered Monoclinic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\cos\beta\hat{\mathbf{x}} + c\sin\beta\hat{\mathbf{z}}\end{aligned}$$



## Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	0	0	(4a)	Ag I
$\mathbf{B}_2$	$\frac{1}{2}\mathbf{a}_3$	$\frac{1}{2}c\cos\beta\hat{\mathbf{x}} + \frac{1}{2}c\sin\beta\hat{\mathbf{z}}$	(4a)	Ag I
$\mathbf{B}_3$	$-y_2\mathbf{a}_1 + y_2\mathbf{a}_2 + \frac{1}{4}\mathbf{a}_3$	$\frac{1}{4}c\cos\beta\hat{\mathbf{x}} + by_2\hat{\mathbf{y}} + \frac{1}{4}c\sin\beta\hat{\mathbf{z}}$	(4e)	Ag II
$\mathbf{B}_4$	$y_2\mathbf{a}_1 - y_2\mathbf{a}_2 + \frac{3}{4}\mathbf{a}_3$	$\frac{3}{4}c\cos\beta\hat{\mathbf{x}} - by_2\hat{\mathbf{y}} + \frac{3}{4}c\sin\beta\hat{\mathbf{z}}$	(4e)	Ag II
$\mathbf{B}_5$	$(x_3 - y_3)\mathbf{a}_1 + (x_3 + y_3)\mathbf{a}_2 + z_3\mathbf{a}_3$	$(ax_3 + cz_3\cos\beta)\hat{\mathbf{x}} + by_3\hat{\mathbf{y}} + cz_3\sin\beta\hat{\mathbf{z}}$	(8f)	S I
$\mathbf{B}_6$	$-(x_3 + y_3)\mathbf{a}_1 - (x_3 - y_3)\mathbf{a}_2 - (z_3 - \frac{1}{2})\mathbf{a}_3$	$-(ax_3 + c(z_3 - \frac{1}{2})\cos\beta)\hat{\mathbf{x}} + by_3\hat{\mathbf{y}} - c(z_3 - \frac{1}{2})\sin\beta\hat{\mathbf{z}}$	(8f)	S I
$\mathbf{B}_7$	$-(x_3 - y_3)\mathbf{a}_1 - (x_3 + y_3)\mathbf{a}_2 - z_3\mathbf{a}_3$	$-(ax_3 + cz_3\cos\beta)\hat{\mathbf{x}} - by_3\hat{\mathbf{y}} - cz_3\sin\beta\hat{\mathbf{z}}$	(8f)	S I
$\mathbf{B}_8$	$(x_3 + y_3)\mathbf{a}_1 + (x_3 - y_3)\mathbf{a}_2 + (z_3 + \frac{1}{2})\mathbf{a}_3$	$(ax_3 + c(z_3 + \frac{1}{2})\cos\beta)\hat{\mathbf{x}} - by_3\hat{\mathbf{y}} + c(z_3 + \frac{1}{2})\sin\beta\hat{\mathbf{z}}$	(8f)	S I
$\mathbf{B}_9$	$(x_4 - y_4)\mathbf{a}_1 + (x_4 + y_4)\mathbf{a}_2 + z_4\mathbf{a}_3$	$(ax_4 + cz_4\cos\beta)\hat{\mathbf{x}} + by_4\hat{\mathbf{y}} + cz_4\sin\beta\hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_{10}$	$-(x_4 + y_4)\mathbf{a}_1 - (x_4 - y_4)\mathbf{a}_2 - (z_4 - \frac{1}{2})\mathbf{a}_3$	$-(ax_4 + c(z_4 - \frac{1}{2})\cos\beta)\hat{\mathbf{x}} + by_4\hat{\mathbf{y}} - c(z_4 - \frac{1}{2})\sin\beta\hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_{11}$	$-(x_4 - y_4)\mathbf{a}_1 - (x_4 + y_4)\mathbf{a}_2 - z_4\mathbf{a}_3$	$-(ax_4 + cz_4\cos\beta)\hat{\mathbf{x}} - by_4\hat{\mathbf{y}} - cz_4\sin\beta\hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_{12}$	$(x_4 + y_4)\mathbf{a}_1 + (x_4 - y_4)\mathbf{a}_2 + (z_4 + \frac{1}{2})\mathbf{a}_3$	$(ax_4 + c(z_4 + \frac{1}{2})\cos\beta)\hat{\mathbf{x}} - by_4\hat{\mathbf{y}} + c(z_4 + \frac{1}{2})\sin\beta\hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_{13}$	$(x_5 - y_5)\mathbf{a}_1 + (x_5 + y_5)\mathbf{a}_2 + z_5\mathbf{a}_3$	$(ax_5 + cz_5\cos\beta)\hat{\mathbf{x}} + by_5\hat{\mathbf{y}} + cz_5\sin\beta\hat{\mathbf{z}}$	(8f)	Sb I
$\mathbf{B}_{14}$	$-(x_5 + y_5)\mathbf{a}_1 - (x_5 - y_5)\mathbf{a}_2 - (z_5 - \frac{1}{2})\mathbf{a}_3$	$-(ax_5 + c(z_5 - \frac{1}{2})\cos\beta)\hat{\mathbf{x}} + by_5\hat{\mathbf{y}} - c(z_5 - \frac{1}{2})\sin\beta\hat{\mathbf{z}}$	(8f)	Sb I
$\mathbf{B}_{15}$	$-(x_5 - y_5)\mathbf{a}_1 - (x_5 + y_5)\mathbf{a}_2 - z_5\mathbf{a}_3$	$-(ax_5 + cz_5\cos\beta)\hat{\mathbf{x}} - by_5\hat{\mathbf{y}} - cz_5\sin\beta\hat{\mathbf{z}}$	(8f)	Sb I
$\mathbf{B}_{16}$	$(x_5 + y_5)\mathbf{a}_1 + (x_5 - y_5)\mathbf{a}_2 + (z_5 + \frac{1}{2})\mathbf{a}_3$	$(ax_5 + c(z_5 + \frac{1}{2})\cos\beta)\hat{\mathbf{x}} - by_5\hat{\mathbf{y}} + c(z_5 + \frac{1}{2})\sin\beta\hat{\mathbf{z}}$	(8f)	Sb I

## References

- [1] H. Effenberger, W. H. Paar, D. Topa, A. J. Criddle, and M. Fleck, *The new mineral baumstarkite and a structural reinvestigation of aramayoite and miargyrite*, Am. Mineral. **87**, 753–764 (2002).

**Found in**

- [1] R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).