


Chalcostibite (CuSbS_2 , $F5_6$) Structure: AB2C_oP16_62_c_2c_c-001

This structure originally had the label AB2C_oP16_62_c_2c_c. Calls to that address will be redirected here.

Cite this page as: M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 1*, Comput. Mater. Sci. **136**, S1-828 (2017). doi: 10.1016/j.commatsci.2017.01.017

<https://aflow.org/p/H6D5>

https://aflow.org/p/AB2C_oP16_62_c_2c_c-001




| | |
|------------------------------------|--|
| Prototype | CuS_2Sb |
| AFLOW prototype label | AB2C_oP16_62_c_2c_c-001 |
| <i>Strukturbericht</i> designation | $F5_6$ |
| Mineral name | chalcostibite |
| ICSD | 171051 |
| Pearson symbol | oP16 |
| Space group number | 62 |
| Space group symbol | $Pnma$ |
| AFLOW prototype command | aflow --proto=AB2C_oP16_62_c_2c_c-001 --params= $a, b/a, c/a, x_1, z_1, x_2, z_2, x_3, z_3, x_4, z_4$ |

Other compounds with this structure
 CuBiS_2

Simple Orthorhombic primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= a \hat{x} \\ \mathbf{a}_2 &= b \hat{y} \\ \mathbf{a}_3 &= c \hat{z} \end{aligned}$$



Basis vectors

| | Lattice coordinates | | Cartesian coordinates | Wyckoff position | Atom type |
|-------------------|--|-----|---|---------------------|--------------|
| \mathbf{B}_1 | $= x_1 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_1 \mathbf{a}_3$ | $=$ | $ax_1 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$ | (4c) | Cu I |
| \mathbf{B}_2 | $= -\left(x_1 - \frac{1}{2}\right) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 +$ $\left(z_1 + \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $-a\left(x_1 - \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c\left(z_1 + \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | Cu I |
| \mathbf{B}_3 | $= -x_1 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_1 \mathbf{a}_3$ | $=$ | $-ax_1 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - cz_1 \hat{\mathbf{z}}$ | (4c) | Cu I |
| \mathbf{B}_4 | $= \left(x_1 + \frac{1}{2}\right) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - \left(z_1 - \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $a\left(x_1 + \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c\left(z_1 - \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | Cu I |
| \mathbf{B}_5 | $= x_2 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_2 \mathbf{a}_3$ | $=$ | $ax_2 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$ | (4c) | S I |
| \mathbf{B}_6 | $= -\left(x_2 - \frac{1}{2}\right) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 +$ $\left(z_2 + \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $-a\left(x_2 - \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c\left(z_2 + \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | S I |
| \mathbf{B}_7 | $= -x_2 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_2 \mathbf{a}_3$ | $=$ | $-ax_2 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$ | (4c) | S I |
| \mathbf{B}_8 | $= \left(x_2 + \frac{1}{2}\right) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - \left(z_2 - \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $a\left(x_2 + \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c\left(z_2 - \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | S I |
| \mathbf{B}_9 | $= x_3 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_3 \mathbf{a}_3$ | $=$ | $ax_3 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$ | (4c) | S II |
| \mathbf{B}_{10} | $= -\left(x_3 - \frac{1}{2}\right) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 +$ $\left(z_3 + \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $-a\left(x_3 - \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c\left(z_3 + \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | S II |
| \mathbf{B}_{11} | $= -x_3 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_3 \mathbf{a}_3$ | $=$ | $-ax_3 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - cz_3 \hat{\mathbf{z}}$ | (4c) | S II |
| \mathbf{B}_{12} | $= \left(x_3 + \frac{1}{2}\right) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - \left(z_3 - \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $a\left(x_3 + \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c\left(z_3 - \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | S II |
| \mathbf{B}_{13} | $= x_4 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_4 \mathbf{a}_3$ | $=$ | $ax_4 \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$ | (4c) | Sb I |
| \mathbf{B}_{14} | $= -\left(x_4 - \frac{1}{2}\right) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 +$ $\left(z_4 + \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $-a\left(x_4 - \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} + c\left(z_4 + \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | Sb I |
| \mathbf{B}_{15} | $= -x_4 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_4 \mathbf{a}_3$ | $=$ | $-ax_4 \hat{\mathbf{x}} + \frac{3}{4} b \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$ | (4c) | Sb I |
| \mathbf{B}_{16} | $= \left(x_4 + \frac{1}{2}\right) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - \left(z_4 - \frac{1}{2}\right) \mathbf{a}_3$ | $=$ | $a\left(x_4 + \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{1}{4} b \hat{\mathbf{y}} - c\left(z_4 - \frac{1}{2}\right) \hat{\mathbf{z}}$ | (4c) | Sb I |

References

- [1] A. Kyono and M. Kimata, *Crystal structures of chalcostibite (CuSbS₂) and emplectite (CuBiS₂): Structural relationship of stereochemical activity between chalcostibite and emplectite*, Am. Mineral. **90**, 162–165 (2005).