


NiO₂ Structure:

AB2_mC6_12_a_i-003

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/DZY0>

https://aflow.org/p/AB2_mC6_12_a_i-003




Prototype	NiO ₂
AFLOW prototype label	AB2_mC6_12_a_i-003
ICSD	88720
Pearson symbol	mC6
Space group number	12
Space group symbol	$C2/m$
AFLOW prototype command	<code>aflow --proto=AB2_mC6_12_a_i-003 --params=a,b/a,c/a,\beta,x2,z2</code>

- C34 Calverite, α -HgO₂, and NiO₂ (this structure) have the same AFLOW prototype label, AB2_mC6_12_a.i. The structures are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Base-centered Monoclinic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\cos\beta\hat{\mathbf{x}} + c\sin\beta\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
B₁ =	0	=	0	(2a)	Ni I
B₂ =	$x_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	=	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(4i)	O I
B₃ =	$-x_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 - z_2 \mathbf{a}_3$	=	$-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} - cz_2 \sin \beta \hat{\mathbf{z}}$	(4i)	O I

References

- [1] J. M. Tarascon, G. Vaughan, Y. Chabre, L. Seguin, M. Anne, P. Strobel, and G. Amatucci, In Situ *Structural and Electrochemical Study of Ni_{1-x}Co_xO₂ Metastable Oxides Prepared by Soft Chemistry*, J. Solid State Chem. **147**, 410–420 (1999), doi:10.1006/jssc.1999.8465.