


# CaSb<sub>2</sub> Structure:

## AB2\_mP6\_11\_e\_2e-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/5Q2X>

[https://aflow.org/p/AB2\\_mP6\\_11\\_e\\_2e-001](https://aflow.org/p/AB2_mP6_11_e_2e-001)



Prototype	CaSb <sub>2</sub>
AFLOW prototype label	AB2_mP6_11_e_2e-001
ICSD	862
Pearson symbol	mP6
Space group number	11
Space group symbol	<i>P</i> 2 <sub>1</sub> /m
AFLOW prototype command	<pre>aflow --proto=AB2_mP6_11_e_2e-001 --params=a,b/a,c/a,\beta,x1,z1,x2,z2,x3,z3</pre>


---

**Other compounds with this structure**  
EuSb<sub>2</sub>, SrSb<sub>2</sub>

---

**Simple Monoclinic primitive vectors**

$$\begin{aligned} \mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}} \end{aligned}$$




---

**Basis vectors**

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1 =$	$x_1 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_1 \mathbf{a}_3$	$(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(2e)	Ca I
$\mathbf{B}_2 =$	$-x_1 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_1 \mathbf{a}_3$	$-(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_1 \sin \beta \hat{\mathbf{z}}$	(2e)	Ca I
$\mathbf{B}_3 =$	$x_2 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_2 \mathbf{a}_3$	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(2e)	Sb I
$\mathbf{B}_4 =$	$-x_2 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_2 \mathbf{a}_3$	$-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_2 \sin \beta \hat{\mathbf{z}}$	(2e)	Sb I
$\mathbf{B}_5 =$	$x_3 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_3 \mathbf{a}_3$	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(2e)	Sb II
$\mathbf{B}_6 =$	$-x_3 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_3 \mathbf{a}_3$	$-(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_3 \sin \beta \hat{\mathbf{z}}$	(2e)	Sb II

## References

- [1] K. Deller and B. Eisenmann, *Darstellung und Kristallstruktur von CaSb<sub>2</sub>*, Z. Anorganische und Allgemeine Chemie **425**, 104–108 (1976), doi:10.1002/zaac.19764250203.

## Found in

- [1] M. Oudah, J. Bannies, D. A. Bonn, and M. C. Aronson, *Superconductivity and Quantum Oscillations in Single Crystals of the Compensated Semimetal CaSb<sub>2</sub>*, Phys. Rev. B **105**, 184504 (2022), doi:10.1103/PhysRevB.105.184504.