


MoP₂ Structure: AB2_oC12_36_a_2a-002

This structure originally had the label AB2_oC12_36_a_2a. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/p/JTSA>

https://aflow.org/p/AB2_oC12_36_a_2a-002



| | |
|-------------------------|--|
| Prototype | MoP ₂ |
| AFLOW prototype label | AB2_oC12_36_a_2a-002 |
| ICSD | 43331 |
| Pearson symbol | oC12 |
| Space group number | 36 |
| Space group symbol | <i>Cmc</i> 2 ₁ |
| AFLOW prototype command | <code>aflow --proto=AB2_oC12_36_a_2a-002</code> <code>--params=a,b/a,c/a,y₁,z₁,y₂,z₂,y₃,z₃</code> |


Other compounds with this structure

WP₂

- An earlier version of this page had the wrong value for the length *c*. We have corrected that in this version.

Base-centered Orthorhombic primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= \frac{1}{2}a \hat{x} - \frac{1}{2}b \hat{y} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{x} + \frac{1}{2}b \hat{y} \\ \mathbf{a}_3 &= c \hat{z} \end{aligned}$$



Basis vectors

| | Lattice coordinates | | Cartesian coordinates | Wyckoff position | Atom type |
|----------------|--|-----|--|---------------------|--------------|
| \mathbf{B}_1 | $= -y_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$ | $=$ | $by_1 \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$ | (4a) | Mo I |
| \mathbf{B}_2 | $= y_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$ | $=$ | $-by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \hat{\mathbf{z}}$ | (4a) | Mo I |
| \mathbf{B}_3 | $= -y_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$ | $=$ | $by_2 \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$ | (4a) | P I |
| \mathbf{B}_4 | $= y_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$ | $=$ | $-by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$ | (4a) | P I |
| \mathbf{B}_5 | $= -y_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$ | $=$ | $by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$ | (4a) | P II |
| \mathbf{B}_6 | $= y_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$ | $=$ | $-by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$ | (4a) | P II |

References

- [1] S. Rundqvist and T. Lundström, *X-Ray Studies of Molybdenum and Tungsten Phosphides*, Acta Chem. Scand. **17**, 37–46 (1962), doi:10.3891/acta.chem.scand.17-0037.