




GdSn₃ Structure:

AB₃_oC16_38_ab_3a3b-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/L5S8>

https://aflow.org/p/AB3_oC16_38_ab_3a3b-001



Prototype GdSn₃

AFLOW prototype label AB₃_oC16_38_ab_3a3b-001

ICSD 104154

Pearson symbol oC16

Space group number 38

Space group symbol *Amm*2

AFLOW prototype command

```
aflow --proto=AB3_oC16_38_ab_3a3b-001
--params=a, b/a, c/a, z1, z2, z3, z4, z5, z6, z7, z8
```


Other compounds with this structure

DySn₃, HoSn₃, ReSn₃, TbSn₃, TmSn₃, YSn₃

- (Palenzona, 1993) identify this as the low-temperature structure of GdSn₃, transforming into the CuAu₃ (*L1*₂) structure at high temperatures.
- (Palenzona, 1993) do not provide the coordinates for this structure within the paper, however ICSD entry 104154 gives the structure and lists this paper as the source.
- Space group *Amm*2 #38 does not specify the origin of the *z*-axis. Here it is fixed by setting *z*₂ = 0 for the Sn-I atom.

Base-centered Orthorhombic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= \frac{1}{2}b \hat{\mathbf{y}} - \frac{1}{2}c \hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{1}{2}b \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates	=	Cartesian coordinates	Wyckoff position	Atom type
B₁ =	$-z_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	=	$cz_1 \hat{\mathbf{z}}$	(2a)	Gd I
B₂ =	$-z_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	=	$cz_2 \hat{\mathbf{z}}$	(2a)	Sn I
B₃ =	$-z_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	=	$cz_3 \hat{\mathbf{z}}$	(2a)	Sn II
B₄ =	$-z_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	=	$cz_4 \hat{\mathbf{z}}$	(2a)	Sn III
B₅ =	$\frac{1}{2} \mathbf{a}_1 - z_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{x}} + cz_5 \hat{\mathbf{z}}$	(2b)	Gd II
B₆ =	$\frac{1}{2} \mathbf{a}_1 - z_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{x}} + cz_6 \hat{\mathbf{z}}$	(2b)	Sn IV
B₇ =	$\frac{1}{2} \mathbf{a}_1 - z_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{x}} + cz_7 \hat{\mathbf{z}}$	(2b)	Sn V
B₈ =	$\frac{1}{2} \mathbf{a}_1 - z_8 \mathbf{a}_2 + z_8 \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{x}} + cz_8 \hat{\mathbf{z}}$	(2b)	Sn VI

References

- [1] A. Palenzona and P. Manfrinetti, *The tin-rich side of the rare earth-tin systems (R = Gd, Tb, Dy, Ho, Er, Tm, Lu and Y)*, J. Alloys Compd. **201**, 43–47 (1993), doi:10.1016/0925-8388(93)90859-L.
- [2] F. Karlsruhe and NIST, *Inorganic Crystal Structure Database*, <http://icsd.fiz-karlsruhe.de/>.