


Model of Ferrite Structure (cI16): AB4C3_cI16_229_a_c_b-001

This structure originally had the label AB4C3_cI16_229_a_c_b. Calls to that address will be redirected here.

Cite this page as: M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 1*, Comput. Mater. Sci. **136**, S1-828 (2017). doi: 10.1016/j.commatsci.2017.01.017

<https://aflow.org/p/YRPB>

https://aflow.org/p/AB4C3_cI16_229_a_c_b-001




| | |
|-------------------------|--------------------------------------------------------------------|
| Prototype | CrFe ₄ Ni ₃ |
| AFLOW prototype label | AB4C3_cI16_229_a_c_b-001 |
| ICSD | none |
| Pearson symbol | cI16 |
| Space group number | 229 |
| Space group symbol | $Im\bar{3}m$ |
| AFLOW prototype command | <pre>aflow --proto=AB4C3_cI16_229_a_c_b-001 --params=a</pre> |

- Ferritic steels are alloys of iron and other metals with an averaged body-centered cubic structure. This model represents one approximation for a ferritic steel. It is not meant to represent a real steel, and the selection of atom types for each Wyckoff position is arbitrary. If we replace the chromium atoms by nickel, this becomes the CsCl (*B2*) with $a_{B2} = 1/4 a$. If we replace both the nickel and chromium atoms by iron, then the structure becomes a body-centered cubic lattice (*A2*) again with $a_{A2} = 1/4 a$.

Body-centered Cubic primitive vectors

a3
a2
a1

$$\begin{aligned}\mathbf{a}_1 &= -\frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}a\hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}a\hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} - \frac{1}{2}a\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

| | Lattice coordinates | | Cartesian coordinates | Wyckoff position | Atom type |
|----------------|-------------------------------------------------------------------------------|-----|-----------------------------------------------------------------------------------------------|------------------|-----------|
| \mathbf{B}_1 | 0 | $=$ | 0 | (2a) | Cr I |
| \mathbf{B}_2 | $\frac{1}{2}\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$ | $=$ | $\frac{1}{2}a\hat{\mathbf{x}}$ | (6b) | Ni I |
| \mathbf{B}_3 | $\frac{1}{2}\mathbf{a}_1 + \frac{1}{2}\mathbf{a}_3$ | $=$ | $\frac{1}{2}a\hat{\mathbf{y}}$ | (6b) | Ni I |
| \mathbf{B}_4 | $\frac{1}{2}\mathbf{a}_1 + \frac{1}{2}\mathbf{a}_2$ | $=$ | $\frac{1}{2}a\hat{\mathbf{z}}$ | (6b) | Ni I |
| \mathbf{B}_5 | $\frac{1}{2}\mathbf{a}_1 + \frac{1}{2}\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$ | $=$ | $\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{y}} + \frac{1}{4}a\hat{\mathbf{z}}$ | (8c) | Fe I |
| \mathbf{B}_6 | $\frac{1}{2}\mathbf{a}_3$ | $=$ | $\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{y}} - \frac{1}{4}a\hat{\mathbf{z}}$ | (8c) | Fe I |
| \mathbf{B}_7 | $\frac{1}{2}\mathbf{a}_2$ | $=$ | $\frac{1}{4}a\hat{\mathbf{x}} - \frac{1}{4}a\hat{\mathbf{y}} + \frac{1}{4}a\hat{\mathbf{z}}$ | (8c) | Fe I |
| \mathbf{B}_8 | $\frac{1}{2}\mathbf{a}_1$ | $=$ | $-\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}a\hat{\mathbf{y}} + \frac{1}{4}a\hat{\mathbf{z}}$ | (8c) | Fe I |

References

- [1] M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW library of crystallographic prototypes: part 1*, Comput. Mater. Sci. **136**, S1–S828 (2017), doi:10.1016/j.commatsci.2017.01.017.