


# Mercury (II) Azide [Hg(N<sub>3</sub>)<sub>2</sub>] Structure: AB6\_oP28\_29\_a\_6a-001

This structure originally had the label AB6\_oP28\_29\_a\_6a. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/p/KSW9>


[https://aflow.org/p/AB6\\_oP28\\_29\\_a\\_6a-001](https://aflow.org/p/AB6_oP28_29_a_6a-001)



<b>Prototype</b>	HgN <sub>6</sub>
<b>AFLOW prototype label</b>	AB6_oP28_29_a_6a-001
<b>Mineral name</b>	Mercury (II) Azide
<b>ICSD</b>	21029
<b>Pearson symbol</b>	oP28
<b>Space group number</b>	29
<b>Space group symbol</b>	<i>Pca</i> 2 <sub>1</sub>
<b>AFLOW prototype command</b>	aflow --proto=AB6_oP28_29_a_6a-001 --params= <i>a, b/a, c/a, x<sub>1</sub>, y<sub>1</sub>, z<sub>1</sub>, x<sub>2</sub>, y<sub>2</sub>, z<sub>2</sub>, x<sub>3</sub>, y<sub>3</sub>, z<sub>3</sub>, x<sub>4</sub>, y<sub>4</sub>, z<sub>4</sub>, x<sub>5</sub>, y<sub>5</sub>, z<sub>5</sub>, x<sub>6</sub>, y<sub>6</sub>, z<sub>6</sub>, x<sub>7</sub>, y<sub>7</sub>, z<sub>7</sub></i>

## Simple Orthorhombic primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= a \hat{x} \\ \mathbf{a}_2 &= b \hat{y} \\ \mathbf{a}_3 &= c \hat{z} \end{aligned}$$



## Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	$=$	$ax_1 \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(4a)	Hg I
$\mathbf{B}_2$	$= -x_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_1 \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Hg I
$\mathbf{B}_3$	$= (x_1 + \frac{1}{2}) \mathbf{a}_1 - y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	$=$	$a(x_1 + \frac{1}{2}) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(4a)	Hg I
$\mathbf{B}_4$	$= -(x_1 - \frac{1}{2}) \mathbf{a}_1 + y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_1 - \frac{1}{2}) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Hg I
$\mathbf{B}_5$	$= x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$ax_2 \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4a)	N I
$\mathbf{B}_6$	$= -x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_2 \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N I
$\mathbf{B}_7$	$= (x_2 + \frac{1}{2}) \mathbf{a}_1 - y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$a(x_2 + \frac{1}{2}) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4a)	N I
$\mathbf{B}_8$	$= -(x_2 - \frac{1}{2}) \mathbf{a}_1 + y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_2 - \frac{1}{2}) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N I
$\mathbf{B}_9$	$= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$ax_3 \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(4a)	N II
$\mathbf{B}_{10}$	$= -x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_3 \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N II
$\mathbf{B}_{11}$	$= (x_3 + \frac{1}{2}) \mathbf{a}_1 - y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$a(x_3 + \frac{1}{2}) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(4a)	N II
$\mathbf{B}_{12}$	$= -(x_3 - \frac{1}{2}) \mathbf{a}_1 + y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_3 - \frac{1}{2}) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N II
$\mathbf{B}_{13}$	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$ax_4 \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(4a)	N III
$\mathbf{B}_{14}$	$= -x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_4 \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N III
$\mathbf{B}_{15}$	$= (x_4 + \frac{1}{2}) \mathbf{a}_1 - y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$a(x_4 + \frac{1}{2}) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(4a)	N III
$\mathbf{B}_{16}$	$= -(x_4 - \frac{1}{2}) \mathbf{a}_1 + y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_4 - \frac{1}{2}) \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N III
$\mathbf{B}_{17}$	$= x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$ax_5 \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(4a)	N IV
$\mathbf{B}_{18}$	$= -x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_5 \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N IV
$\mathbf{B}_{19}$	$= (x_5 + \frac{1}{2}) \mathbf{a}_1 - y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$a(x_5 + \frac{1}{2}) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(4a)	N IV
$\mathbf{B}_{20}$	$= -(x_5 - \frac{1}{2}) \mathbf{a}_1 + y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_5 - \frac{1}{2}) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N IV
$\mathbf{B}_{21}$	$= x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	$=$	$ax_6 \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(4a)	N V
$\mathbf{B}_{22}$	$= -x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_6 \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N V
$\mathbf{B}_{23}$	$= (x_6 + \frac{1}{2}) \mathbf{a}_1 - y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	$=$	$a(x_6 + \frac{1}{2}) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(4a)	N V
$\mathbf{B}_{24}$	$= -(x_6 - \frac{1}{2}) \mathbf{a}_1 + y_6 \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_6 - \frac{1}{2}) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N V
$\mathbf{B}_{25}$	$= x_7 \mathbf{a}_1 + y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	$=$	$ax_7 \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + cz_7 \hat{\mathbf{z}}$	(4a)	N VI
$\mathbf{B}_{26}$	$= -x_7 \mathbf{a}_1 - y_7 \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-ax_7 \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N VI
$\mathbf{B}_{27}$	$= (x_7 + \frac{1}{2}) \mathbf{a}_1 - y_7 \mathbf{a}_2 + z_7 \mathbf{a}_3$	$=$	$a(x_7 + \frac{1}{2}) \hat{\mathbf{x}} - by_7 \hat{\mathbf{y}} + cz_7 \hat{\mathbf{z}}$	(4a)	N VI
$\mathbf{B}_{28}$	$= -(x_7 - \frac{1}{2}) \mathbf{a}_1 + y_7 \mathbf{a}_2 + (z_7 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a(x_7 - \frac{1}{2}) \hat{\mathbf{x}} + by_7 \hat{\mathbf{y}} + c(z_7 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	N VI

## References

- [1] U. Müller, *Die Kristallstruktur von  $\alpha$ -Quecksilber(II)-Azid*, Z. Anorganische und Allgemeine Chemie **399**, 183–192 (1973), doi:10.1002/zaac.19733990207.

**Found in**

- [1] T. B. Massalski, H. Okamoto, P. R. Subramanian, and L. Kacprzak, eds., *Binary Alloy Phase Diagrams*, vol. 3 (ASM International, Materials Park, Ohio, USA, 1990), 2<sup>nd</sup> edn. Hf-Re to Zn-Zr.