


# NiMoP<sub>2</sub> Structure: ABC2\_hP8\_194\_b\_a\_f-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/D1PM>

[https://aflow.org/p/ABC2\\_hP8\\_194\\_b\\_a\\_f-001](https://aflow.org/p/ABC2_hP8_194_b_a_f-001)



Prototype	MoNiP <sub>2</sub>
AFLOW prototype label	ABC2_hP8_194_b_a_f-001
ICSD	76283
Pearson symbol	hP8
Space group number	194
Space group symbol	<i>P</i> 6 <sub>3</sub> / <i>m</i> <i>m</i> <i>c</i>
AFLOW prototype command	<code>aflow --proto=ABC2_hP8_194_b_a_f-001 --params=a, c/a, z<sub>3</sub></code>

## Other compounds with this structure


CoMoP<sub>2</sub>, CoWP<sub>2</sub>, NiWP<sub>2</sub>

## Hexagonal primitive vectors

$$\mathbf{a}_1 = \frac{1}{2}a \hat{x} - \frac{\sqrt{3}}{2}a \hat{y}$$

$$\mathbf{a}_2 = \frac{1}{2}a \hat{x} + \frac{\sqrt{3}}{2}a \hat{y}$$

$$\mathbf{a}_3 = c \hat{z}$$



---

## Basis vectors

	Lattice coordinates	=	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	=	$0$	=	$0$	(2a) Ni I
$\mathbf{B}_2$	=	$\frac{1}{2} \mathbf{a}_3$	=	$\frac{1}{2} c \hat{\mathbf{z}}$	(2a) Ni I
$\mathbf{B}_3$	=	$\frac{1}{4} \mathbf{a}_3$	=	$\frac{1}{4} c \hat{\mathbf{z}}$	(2b) Mn I
$\mathbf{B}_4$	=	$\frac{3}{4} \mathbf{a}_3$	=	$\frac{3}{4} c \hat{\mathbf{z}}$	(2b) Mn I
$\mathbf{B}_5$	=	$\frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + z_3 \mathbf{a}_3$	=	$\frac{1}{2} a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6} a \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(4f) P I
$\mathbf{B}_6$	=	$\frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	=	$\frac{1}{2} a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6} a \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4f) P I
$\mathbf{B}_7$	=	$\frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 - z_3 \mathbf{a}_3$	=	$\frac{1}{2} a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6} a \hat{\mathbf{y}} - cz_3 \hat{\mathbf{z}}$	(4f) P I
$\mathbf{B}_8$	=	$\frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	=	$\frac{1}{2} a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6} a \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \hat{\mathbf{z}}$	(4f) P I

## References

- [1] R. Guérin and M. Sergent, *Nouveau phosphure ternaire: NiMoP<sub>2</sub>, a chaîne linéaire infinie -Mo-Ni-Mo- et composés isotypes: NiWP<sub>2</sub>, CoMoP<sub>2</sub> et CoWP<sub>2</sub>*, J. Solid State Chem. **18**, 317–323 (1976), doi:10.1016/0022-4596(76)90113-4.