


CoGeO₃ Structure: ABC3_mC40_15_2e_f_3f-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/6YLQ>

https://aflow.org/p/ABC3_mC40_15_2e_f_3f-001



Prototype	CoGeO ₃
AFLOW prototype label	ABC3_mC40_15_2e_f_3f-001
ICSD	26814
Pearson symbol	mC40
Space group number	15
Space group symbol	$C2/c$
AFLOW prototype command	<code>aflow --proto=ABC3_mC40_15_2e_f_3f-001 --params=a,b/a,c/a,\beta,y1,y2,x3,y3,z3,x4,y4,z4,x5,y5,z5,x6,y6,z6</code>

Other compounds with this structure


MgGeO₃

- This is the ground state structure of CoGeO₃. Above 1351°C it transforms to the tetragonal MgSiO₃ ($S4_3$) structure, which remains metastable down to 4K (Zhao, 2021).
- The crystal structure data was taken at 4K.
- There is no ICSD or CCDC entry for (Redhammer, 2010). Instead we use the ICSD from the much older work of (Peacor, 1968).

Base-centered Monoclinic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}b\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\cos\beta\hat{\mathbf{x}} + c\sin\beta\hat{\mathbf{z}}\end{aligned}$$

\mathbf{a}_3
 \mathbf{a}_2
 \mathbf{a}_1



Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	$-y_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$\frac{1}{4}c\cos\beta\hat{\mathbf{x}} + by_1\hat{\mathbf{y}} + \frac{1}{4}c\sin\beta\hat{\mathbf{z}}$	(4e)	Co I
\mathbf{B}_2	$y_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$\frac{3}{4}c\cos\beta\hat{\mathbf{x}} - by_1\hat{\mathbf{y}} + \frac{3}{4}c\sin\beta\hat{\mathbf{z}}$	(4e)	Co I
\mathbf{B}_3	$-y_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$\frac{1}{4}c\cos\beta\hat{\mathbf{x}} + by_2\hat{\mathbf{y}} + \frac{1}{4}c\sin\beta\hat{\mathbf{z}}$	(4e)	Co II
\mathbf{B}_4	$y_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$\frac{3}{4}c\cos\beta\hat{\mathbf{x}} - by_2\hat{\mathbf{y}} + \frac{3}{4}c\sin\beta\hat{\mathbf{z}}$	(4e)	Co II
\mathbf{B}_5	$(x_3 - y_3) \mathbf{a}_1 + (x_3 + y_3) \mathbf{a}_2 + z_3 \mathbf{a}_3$	$(ax_3 + cz_3 \cos\beta)\hat{\mathbf{x}} + by_3\hat{\mathbf{y}} + cz_3 \sin\beta\hat{\mathbf{z}}$	(8f)	Ge I
\mathbf{B}_6	$-(x_3 + y_3) \mathbf{a}_1 - (x_3 - y_3) \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_3 + c(z_3 - \frac{1}{2}) \cos\beta)\hat{\mathbf{x}} + by_3\hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \sin\beta\hat{\mathbf{z}}$	(8f)	Ge I
\mathbf{B}_7	$-(x_3 - y_3) \mathbf{a}_1 - (x_3 + y_3) \mathbf{a}_2 - z_3 \mathbf{a}_3$	$-(ax_3 + cz_3 \cos\beta)\hat{\mathbf{x}} - by_3\hat{\mathbf{y}} - cz_3 \sin\beta\hat{\mathbf{z}}$	(8f)	Ge I
\mathbf{B}_8	$(x_3 + y_3) \mathbf{a}_1 + (x_3 - y_3) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$(ax_3 + c(z_3 + \frac{1}{2}) \cos\beta)\hat{\mathbf{x}} - by_3\hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \sin\beta\hat{\mathbf{z}}$	(8f)	Ge I
\mathbf{B}_9	$(x_4 - y_4) \mathbf{a}_1 + (x_4 + y_4) \mathbf{a}_2 + z_4 \mathbf{a}_3$	$(ax_4 + cz_4 \cos\beta)\hat{\mathbf{x}} + by_4\hat{\mathbf{y}} + cz_4 \sin\beta\hat{\mathbf{z}}$	(8f)	O I
\mathbf{B}_{10}	$-(x_4 + y_4) \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_4 + c(z_4 - \frac{1}{2}) \cos\beta)\hat{\mathbf{x}} + by_4\hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \sin\beta\hat{\mathbf{z}}$	(8f)	O I
\mathbf{B}_{11}	$-(x_4 - y_4) \mathbf{a}_1 - (x_4 + y_4) \mathbf{a}_2 - z_4 \mathbf{a}_3$	$-(ax_4 + cz_4 \cos\beta)\hat{\mathbf{x}} - by_4\hat{\mathbf{y}} - cz_4 \sin\beta\hat{\mathbf{z}}$	(8f)	O I
\mathbf{B}_{12}	$(x_4 + y_4) \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$(ax_4 + c(z_4 + \frac{1}{2}) \cos\beta)\hat{\mathbf{x}} - by_4\hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \sin\beta\hat{\mathbf{z}}$	(8f)	O I
\mathbf{B}_{13}	$(x_5 - y_5) \mathbf{a}_1 + (x_5 + y_5) \mathbf{a}_2 + z_5 \mathbf{a}_3$	$(ax_5 + cz_5 \cos\beta)\hat{\mathbf{x}} + by_5\hat{\mathbf{y}} + cz_5 \sin\beta\hat{\mathbf{z}}$	(8f)	O II
\mathbf{B}_{14}	$-(x_5 + y_5) \mathbf{a}_1 - (x_5 - y_5) \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_5 + c(z_5 - \frac{1}{2}) \cos\beta)\hat{\mathbf{x}} + by_5\hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \sin\beta\hat{\mathbf{z}}$	(8f)	O II
\mathbf{B}_{15}	$-(x_5 - y_5) \mathbf{a}_1 - (x_5 + y_5) \mathbf{a}_2 - z_5 \mathbf{a}_3$	$-(ax_5 + cz_5 \cos\beta)\hat{\mathbf{x}} - by_5\hat{\mathbf{y}} - cz_5 \sin\beta\hat{\mathbf{z}}$	(8f)	O II
\mathbf{B}_{16}	$(x_5 + y_5) \mathbf{a}_1 + (x_5 - y_5) \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$(ax_5 + c(z_5 + \frac{1}{2}) \cos\beta)\hat{\mathbf{x}} - by_5\hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \sin\beta\hat{\mathbf{z}}$	(8f)	O II
\mathbf{B}_{17}	$(x_6 - y_6) \mathbf{a}_1 + (x_6 + y_6) \mathbf{a}_2 + z_6 \mathbf{a}_3$	$(ax_6 + cz_6 \cos\beta)\hat{\mathbf{x}} + by_6\hat{\mathbf{y}} + cz_6 \sin\beta\hat{\mathbf{z}}$	(8f)	O III
\mathbf{B}_{18}	$-(x_6 + y_6) \mathbf{a}_1 - (x_6 - y_6) \mathbf{a}_2 - (z_6 - \frac{1}{2}) \mathbf{a}_3$	$-(ax_6 + c(z_6 - \frac{1}{2}) \cos\beta)\hat{\mathbf{x}} + by_6\hat{\mathbf{y}} - c(z_6 - \frac{1}{2}) \sin\beta\hat{\mathbf{z}}$	(8f)	O III

$$\mathbf{B}_{19} = -(x_6 - y_6) \mathbf{a}_1 - (x_6 + y_6) \mathbf{a}_2 - z_6 \mathbf{a}_3 = -(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} - cz_6 \sin \beta \hat{\mathbf{z}} \quad (8f) \quad \text{O III}$$

$$\mathbf{B}_{20} = (x_6 + y_6) \mathbf{a}_1 + (x_6 - y_6) \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3 = (ax_6 + c(z_6 + \frac{1}{2}) \cos \beta) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \sin \beta \hat{\mathbf{z}} \quad (8f) \quad \text{O III}$$

References

- [1] G. J. Redhammer, A. Senyshyn, G. Tippelt, C. Pietzonka, G. Roth, and G. Amthauer, *Magnetic and nuclear structure and thermal expansion of orthorhombic and monoclinic polymorphs of CoGeO₃ pyroxene*, Phys. Chem. Minerals **37**, 311–332 (2010), doi:10.1007/s00269-009-0335-x.
- [2] D. R. Peacor, *The crystal structure of CoGeO₃*, Z. Krystallogr. **126**, 299–306 (1968), doi:10.1524/zkri.1968.126.16.299.