$NbNiTe_5$ Structure: ABC5_oC28_63_c_a_c2f-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

https://aflow.org/p/BN2Z

https://aflow.org/p/ABC5_oC28_63_c_a_c2f-001



Prototype	$NbNiTe_5$
AFLOW prototype label	ABC5_oC28_63_c_a_c2f-001
ICSD	73316
Pearson symbol	oC28
Space group number	63
Space group symbol	$Cmcm$
AFLOW prototype command	`aflow --proto=ABC5_oC28_63_c_a_c2f-001 --params=`$a, b/a, c/a, y_2, y_3, y_4, z_4, y_5, z_5$

Other compounds with this structure
$LaMgTe_5$, $TaNiTe_5$, $TaPtTe_5$

Base-centered Orthorhombic primitive vectors

$$\mathbf{a_1} = \tfrac{1}{2}a\,\hat{\mathbf{x}} - \tfrac{1}{2}b\,\hat{\mathbf{y}}$$
$$\mathbf{a_2} = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}b\,\hat{\mathbf{y}}$$
$$\mathbf{a_3} = c\,\hat{\mathbf{z}}$$



Basis vectors

		Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B_1}$	=	0	=	0	(4a)	Ni I
$\mathbf{B_2}$	=	$\frac{1}{2}\,\mathbf{a}_3$	=	$\frac{1}{2}c\,\hat{\mathbf{z}}$	(4a)	Ni I
$\mathbf{B_3}$	=	$-y_2\,\mathbf{a}_1 + y_2\,\mathbf{a}_2 + \frac{1}{4}\,\mathbf{a}_3$	=	$by_2\,\hat{\mathbf{y}} + \frac{1}{4}c\,\hat{\mathbf{z}}$	(4c)	Nb I
$\mathbf{B_4}$	=	$y_2\,\mathbf{a}_1 - y_2\,\mathbf{a}_2 + \frac{3}{4}\,\mathbf{a}_3$	=	$-by_2\,\hat{\mathbf{y}} + \frac{3}{4}c\,\hat{\mathbf{z}}$	(4c)	Nb I
$\mathbf{B_5}$	=	$-y_3\,\mathbf{a}_1 + y_3\,\mathbf{a}_2 + \frac{1}{4}\,\mathbf{a}_3$	=	$by_3\,\hat{\mathbf{y}} + \frac{1}{4}c\,\hat{\mathbf{z}}$	(4c)	Te I
$\mathbf{B_6}$	=	$y_3\,\mathbf{a}_1 - y_3\,\mathbf{a}_2 + \frac{3}{4}\,\mathbf{a}_3$	=	$-by_3\,\hat{\mathbf{y}} + \frac{3}{4}c\,\hat{\mathbf{z}}$	(4c)	Te I
$\mathbf{B_7}$	=	$-y_4\,\mathbf{a}_1 + y_4\,\mathbf{a}_2 + z_4\,\mathbf{a}_3$	=	$by_4\,\hat{\mathbf{y}} + cz_4\,\hat{\mathbf{z}}$	(8f)	Te II
$\mathbf{B_8}$	=	$y_4\,\mathbf{a}_1 - y_4\,\mathbf{a}_2 + \left(z_4 + \frac{1}{2}\right)\,\mathbf{a}_3$	=	$-by_4\,\hat{\mathbf{y}} + c\left(z_4 + \frac{1}{2}\right)\,\hat{\mathbf{z}}$	(8f)	Te II
$\mathbf{B_9}$	=	$-y_4\,\mathbf{a}_1 + y_4\,\mathbf{a}_2 - \left(z_4 - \frac{1}{2}\right)\,\mathbf{a}_3$	=	$by_4\,\hat{\mathbf{y}} - c\left(z_4 - \frac{1}{2}\right)\,\hat{\mathbf{z}}$	(8f)	Te II
$\mathbf{B_{10}}$	=	$y_4\,\mathbf{a}_1 - y_4\,\mathbf{a}_2 - z_4\,\mathbf{a}_3$	=	$-by_4\,\hat{\mathbf{y}} - cz_4\,\hat{\mathbf{z}}$	(8f)	Te II
$\mathbf{B_{11}}$	=	$-y_5\,\mathbf{a}_1 + y_5\,\mathbf{a}_2 + z_5\,\mathbf{a}_3$	=	$by_5\,\hat{\mathbf{y}} + cz_5\,\hat{\mathbf{z}}$	(8f)	Te III
$\mathbf{B_{12}}$	=	$y_5\,\mathbf{a}_1 - y_5\,\mathbf{a}_2 + \left(z_5 + \frac{1}{2}\right)\,\mathbf{a}_3$	=	$-by_5\,\hat{\mathbf{y}} + c\left(z_5 + \frac{1}{2}\right)\,\hat{\mathbf{z}}$	(8f)	Te III
$\mathbf{B_{13}}$	=	$-y_5\,\mathbf{a}_1 + y_5\,\mathbf{a}_2 - \left(z_5 - \frac{1}{2}\right)\,\mathbf{a}_3$	=	$by_5\,\hat{\mathbf{y}} - c\left(z_5 - \frac{1}{2}\right)\,\hat{\mathbf{z}}$	(8f)	Te III
$\mathbf{B_{14}}$	=	$y_5\,\mathbf{a}_1 - y_5\,\mathbf{a}_2 - z_5\,\mathbf{a}_3$	=	$-by_5\,\hat{\mathbf{y}} - cz_5\,\hat{\mathbf{z}}$	(8f)	Te III

References

[1] E. W. Liimatta and J. A. Ibers, *Synthesis, structure, and physical properties of the new layered ternary chalcogenide $NbNiTe_5$*, J. Solid State Chem. **71**, 384–389 (1987), doi:10.1016/0022-4596(87)90246-5.