


# Covellite ( $\text{CuS}$ , $B18$ ) Structure: AB\_hP12\_194\_cf\_de-001

This structure originally had the label `AB_hP12_194_df_ce`. Calls to that address will be redirected here.

Cite this page as: M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 1*, Comput. Mater. Sci. **136**, S1-828 (2017). doi: 10.1016/j.commatsci.2017.01.017

<https://aflow.org/p/QP0Q>

[https://aflow.org/p/AB\\_hP12\\_194\\_cf\\_de-001](https://aflow.org/p/AB_hP12_194_cf_de-001)



<b>Prototype</b>	$\text{CuS}$
<b>AFLOW prototype label</b>	<code>AB_hP12_194_cf_de-001</code>
<b>Strukturbericht designation</b>	$B18$
<b>Mineral name</b>	covellite
<b>ICSD</b>	41975
<b>Pearson symbol</b>	$hP12$
<b>Space group number</b>	194
<b>Space group symbol</b>	$P6_3/mmc$
<b>AFLOW prototype command</b>	<code>aflow --proto=AB_hP12_194_cf_de-001 --params=a, c/a, z<sub>3</sub>, z<sub>4</sub></code>

---

## Other compounds with this structure


CuSe

---

- We did not find an ICSD entry for (Ohmasa, 1977), so we one from (Kalbskopf, 1975) which is quoated our source paper.

## Hexagonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\hat{\mathbf{z}}\end{aligned}$$



## Basis vectors

	Lattice coordinates	=	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$\frac{1}{3}\mathbf{a}_1 + \frac{2}{3}\mathbf{a}_2 + \frac{1}{4}\mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + \frac{1}{4}c\hat{\mathbf{z}}$	(2c)	Cu I
$\mathbf{B}_2$	$\frac{2}{3}\mathbf{a}_1 + \frac{1}{3}\mathbf{a}_2 + \frac{3}{4}\mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + \frac{3}{4}c\hat{\mathbf{z}}$	(2c)	Cu I
$\mathbf{B}_3$	$\frac{1}{3}\mathbf{a}_1 + \frac{2}{3}\mathbf{a}_2 + \frac{3}{4}\mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + \frac{3}{4}c\hat{\mathbf{z}}$	(2d)	S I
$\mathbf{B}_4$	$\frac{2}{3}\mathbf{a}_1 + \frac{1}{3}\mathbf{a}_2 + \frac{1}{4}\mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + \frac{1}{4}c\hat{\mathbf{z}}$	(2d)	S I
$\mathbf{B}_5$	$z_3 \mathbf{a}_3$	=	$cz_3 \hat{\mathbf{z}}$	(4e)	S II
$\mathbf{B}_6$	$(z_3 + \frac{1}{2}) \mathbf{a}_3$	=	$c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4e)	S II
$\mathbf{B}_7$	$-z_3 \mathbf{a}_3$	=	$-cz_3 \hat{\mathbf{z}}$	(4e)	S II
$\mathbf{B}_8$	$-(z_3 - \frac{1}{2}) \mathbf{a}_3$	=	$-c(z_3 - \frac{1}{2}) \hat{\mathbf{z}}$	(4e)	S II
$\mathbf{B}_9$	$\frac{1}{3}\mathbf{a}_1 + \frac{2}{3}\mathbf{a}_2 + z_4 \mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(4f)	Cu II
$\mathbf{B}_{10}$	$\frac{2}{3}\mathbf{a}_1 + \frac{1}{3}\mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4f)	Cu II
$\mathbf{B}_{11}$	$\frac{2}{3}\mathbf{a}_1 + \frac{1}{3}\mathbf{a}_2 - z_4 \mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(4f)	Cu II
$\mathbf{B}_{12}$	$\frac{1}{3}\mathbf{a}_1 + \frac{2}{3}\mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(4f)	Cu II

## References

- [1] M. Ohmasa, M. Suzuki, and Y. Takéuchi, *A refinement of the crystal structure of covellite, CuS*, Mineralogical Journal **8**, 311–319 (1977), doi:10.2465/minerj.8.311.
- [2] R. Kalbskopf, F. Pertlik, and J. Zeman, *Verfeinerung des Kristallstruktur des Covellins, Cu S, mit Einkristalldaten*, TMPM Tschermaks Min. Petr. Mitt. **22**, 242–249 (1975).