


Cinnabar (HgS , $B9$) Structure: AB_hP6_154_a_b-001

This structure originally had the label AB_hP6_154_a_b. Calls to that address will be redirected here.

Cite this page as: M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 1*, Comput. Mater. Sci. **136**, S1-828 (2017). doi: 10.1016/j.commatsci.2017.01.017

<https://aflow.org/p/A3TK>

https://aflow.org/p/AB_hP6_154_a_b-001




Prototype	HgS
AFLOW prototype label	AB_hP6_154_a_b-001
<i>Strukturbericht</i> designation	$B9$
Mineral name	cinnabar
ICSD	70054
Pearson symbol	hP6
Space group number	154
Space group symbol	$P\bar{3}21$
AFLOW prototype command	<pre>aflow --proto=AB_hP6_154_a_b-001 --params=a, c/a, x1, x2</pre>

Other compounds with this structure

HgO

Trigonal (Hexagonal) primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates	=	Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1 =	$x_1 \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_3$	=	$\frac{1}{2}ax_1\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_1\hat{\mathbf{y}} + \frac{2}{3}c\hat{\mathbf{z}}$	(3a)	Hg I
\mathbf{B}_2 =	$x_1 \mathbf{a}_2 + \frac{1}{3} \mathbf{a}_3$	=	$\frac{1}{2}ax_1\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_1\hat{\mathbf{y}} + \frac{1}{3}c\hat{\mathbf{z}}$	(3a)	Hg I
\mathbf{B}_3 =	$-x_1 \mathbf{a}_1 - x_1 \mathbf{a}_2$	=	$-ax_1\hat{\mathbf{x}}$	(3a)	Hg I
\mathbf{B}_4 =	$x_2 \mathbf{a}_1 + \frac{1}{6} \mathbf{a}_3$	=	$\frac{1}{2}ax_2\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_2\hat{\mathbf{y}} + \frac{1}{6}c\hat{\mathbf{z}}$	(3b)	S I
\mathbf{B}_5 =	$x_2 \mathbf{a}_2 + \frac{5}{6} \mathbf{a}_3$	=	$\frac{1}{2}ax_2\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_2\hat{\mathbf{y}} + \frac{5}{6}c\hat{\mathbf{z}}$	(3b)	S I
\mathbf{B}_6 =	$-x_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	=	$-ax_2\hat{\mathbf{x}} + \frac{1}{2}c\hat{\mathbf{z}}$	(3b)	S I

References

- [1] P. Auvray and F. Genet, *Affinement de la structure cristalline du cinabre α -HgS*, Bull. Soc. fr. Minéral. Crystallogr. **96**, 218–219 (1973).

Found in

- [1] R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).