

NaP Structure:


AB_oP16_19_2a_2a-001

This structure originally had the label AB_oP16_19_2a_2a. Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/p/MEBJ>

https://aflow.org/p/AB_oP16_19_2a_2a-001




Prototype	NaP
AFLOW prototype label	AB_oP16_19_2a_2a-001
ICSD	14009
Pearson symbol	oP16
Space group number	19
Space group symbol	$P2_12_12_1$
AFLOW prototype command	<code>aflow --proto=AB_oP16_19_2a_2a-001 --params=a, b/a, c/a, x1, y1, z1, x2, y2, z2, x3, y3, z3, x4, y4, z4</code>

Other compounds with this structure

CsSb, KP, RbSb

Simple Orthorhombic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates	=	Cartesian coordinates	Wyckoff position	Atom type
\mathbf{B}_1	$x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	=	$ax_1 \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(4a)	Na I
\mathbf{B}_2	$-(x_1 - \frac{1}{2}) \mathbf{a}_1 - y_1 \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_1 - \frac{1}{2}) \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Na I
\mathbf{B}_3	$-x_1 \mathbf{a}_1 + (y_1 + \frac{1}{2}) \mathbf{a}_2 - (z_1 - \frac{1}{2}) \mathbf{a}_3$	=	$-ax_1 \hat{\mathbf{x}} + b(y_1 + \frac{1}{2}) \hat{\mathbf{y}} - c(z_1 - \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Na I
\mathbf{B}_4	$(x_1 + \frac{1}{2}) \mathbf{a}_1 - (y_1 - \frac{1}{2}) \mathbf{a}_2 - z_1 \mathbf{a}_3$	=	$a(x_1 + \frac{1}{2}) \hat{\mathbf{x}} - b(y_1 - \frac{1}{2}) \hat{\mathbf{y}} - cz_1 \hat{\mathbf{z}}$	(4a)	Na I
\mathbf{B}_5	$x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	=	$ax_2 \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4a)	Na II
\mathbf{B}_6	$-(x_2 - \frac{1}{2}) \mathbf{a}_1 - y_2 \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_2 - \frac{1}{2}) \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Na II
\mathbf{B}_7	$-x_2 \mathbf{a}_1 + (y_2 + \frac{1}{2}) \mathbf{a}_2 - (z_2 - \frac{1}{2}) \mathbf{a}_3$	=	$-ax_2 \hat{\mathbf{x}} + b(y_2 + \frac{1}{2}) \hat{\mathbf{y}} - c(z_2 - \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	Na II
\mathbf{B}_8	$(x_2 + \frac{1}{2}) \mathbf{a}_1 - (y_2 - \frac{1}{2}) \mathbf{a}_2 - z_2 \mathbf{a}_3$	=	$a(x_2 + \frac{1}{2}) \hat{\mathbf{x}} - b(y_2 - \frac{1}{2}) \hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$	(4a)	Na II
\mathbf{B}_9	$x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	=	$ax_3 \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(4a)	P I
\mathbf{B}_{10}	$-(x_3 - \frac{1}{2}) \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_3 - \frac{1}{2}) \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	P I
\mathbf{B}_{11}	$-x_3 \mathbf{a}_1 + (y_3 + \frac{1}{2}) \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	=	$-ax_3 \hat{\mathbf{x}} + b(y_3 + \frac{1}{2}) \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	P I
\mathbf{B}_{12}	$(x_3 + \frac{1}{2}) \mathbf{a}_1 - (y_3 - \frac{1}{2}) \mathbf{a}_2 - z_3 \mathbf{a}_3$	=	$a(x_3 + \frac{1}{2}) \hat{\mathbf{x}} - b(y_3 - \frac{1}{2}) \hat{\mathbf{y}} - cz_3 \hat{\mathbf{z}}$	(4a)	P I
\mathbf{B}_{13}	$x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	=	$ax_4 \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(4a)	P II
\mathbf{B}_{14}	$-(x_4 - \frac{1}{2}) \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_4 - \frac{1}{2}) \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	P II
\mathbf{B}_{15}	$-x_4 \mathbf{a}_1 + (y_4 + \frac{1}{2}) \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	=	$-ax_4 \hat{\mathbf{x}} + b(y_4 + \frac{1}{2}) \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(4a)	P II
\mathbf{B}_{16}	$(x_4 + \frac{1}{2}) \mathbf{a}_1 - (y_4 - \frac{1}{2}) \mathbf{a}_2 - z_4 \mathbf{a}_3$	=	$a(x_4 + \frac{1}{2}) \hat{\mathbf{x}} - b(y_4 - \frac{1}{2}) \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(4a)	P II

References

- [1] H. G. von Schnerring and W. Höngle, *Zur Chemie und Strukturchemie der Phosphide und Polyphosphide. 20. Darstellung, Struktur und Eigenschaften der Alkalimetallmonophosphide NaP und KP*, Z. Anorganische und Allgemeine Chemie **456**, 194–206 (1979), doi:10.1002/zaac.19794560121.

Found in

- [1] P. Villars, *NaP Crystal Structure* (2016). PAULING FILE in: Inorganic Solid Phases, SpringerMaterials (online database).