





# Empressite (AgTe) Structure: AB\_oP32\_62\_2cd\_2cd-001

Cite this page as: H. Eckert, S. Divilov, A. Zettel, M. J. Mehl, D. Hicks, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*. In preparation.

<https://aflow.org/p/JH5H>

[https://aflow.org/p/AB\\_oP32\\_62\\_2cd\\_2cd-001](https://aflow.org/p/AB_oP32_62_2cd_2cd-001)

Ag  
Te



Prototype	AgTe
AFLOW prototype label	AB_oP32_62_2cd_2cd-001
Mineral name	empressite
ICSD	55237
Pearson symbol	oP32
Space group number	62
Space group symbol	<i>Pnma</i>
AFLOW prototype command	<pre>aflow --proto=AB_oP32_62_2cd_2cd-001 --params=a,b/a,c/a,x1,z1,x2,z2,x3,z3,x4,z4,x5,y5,z5,x6,y6,z6</pre>

- (Bindi, 2004) give the structural information in the *Pmnb* setting of space group #62. We used FINDSYM to transform this to the standard *Pnma* setting.


## Simple Orthorhombic primitive vectors

$$\mathbf{a}_1 = a \hat{\mathbf{x}}$$

$$\mathbf{a}_2 = b \hat{\mathbf{y}}$$

$$\mathbf{a}_3 = c \hat{\mathbf{z}}$$

$\mathbf{a}_1$   
 $\mathbf{a}_2$   
 $\mathbf{a}_3$



## Basis vectors

	Lattice coordinates	=	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$x_1 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_1 \mathbf{a}_3$	=	$ax_1 \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(4c)	Ag I
$\mathbf{B}_2$	$-(x_1 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_1 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} + c(z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Ag I
$\mathbf{B}_3$	$-x_1 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_1 \mathbf{a}_3$	=	$-ax_1 \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_1 \hat{\mathbf{z}}$	(4c)	Ag I
$\mathbf{B}_4$	$(x_1 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_1 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_1 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} - c(z_1 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Ag I
$\mathbf{B}_5$	$x_2 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_2 \mathbf{a}_3$	=	$ax_2 \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4c)	Ag II
$\mathbf{B}_6$	$-(x_2 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_2 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Ag II
$\mathbf{B}_7$	$-x_2 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_2 \mathbf{a}_3$	=	$-ax_2 \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$	(4c)	Ag II
$\mathbf{B}_8$	$(x_2 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_2 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_2 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} - c(z_2 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Ag II
$\mathbf{B}_9$	$x_3 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_3 \mathbf{a}_3$	=	$ax_3 \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(4c)	Te I
$\mathbf{B}_{10}$	$-(x_3 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_3 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Te I
$\mathbf{B}_{11}$	$-x_3 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_3 \mathbf{a}_3$	=	$-ax_3 \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_3 \hat{\mathbf{z}}$	(4c)	Te I
$\mathbf{B}_{12}$	$(x_3 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_3 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Te I
$\mathbf{B}_{13}$	$x_4 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_4 \mathbf{a}_3$	=	$ax_4 \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(4c)	Te II
$\mathbf{B}_{14}$	$-(x_4 - \frac{1}{2}) \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_4 - \frac{1}{2}) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Te II
$\mathbf{B}_{15}$	$-x_4 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_4 \mathbf{a}_3$	=	$-ax_4 \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(4c)	Te II
$\mathbf{B}_{16}$	$(x_4 + \frac{1}{2}) \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_4 + \frac{1}{2}) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(4c)	Te II
$\mathbf{B}_{17}$	$x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	=	$ax_5 \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{18}$	$-(x_5 - \frac{1}{2}) \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_5 - \frac{1}{2}) \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{19}$	$-x_5 \mathbf{a}_1 + (y_5 + \frac{1}{2}) \mathbf{a}_2 - z_5 \mathbf{a}_3$	=	$-ax_5 \hat{\mathbf{x}} + b(y_5 + \frac{1}{2}) \hat{\mathbf{y}} - cz_5 \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{20}$	$(x_5 + \frac{1}{2}) \mathbf{a}_1 - (y_5 - \frac{1}{2}) \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_5 + \frac{1}{2}) \hat{\mathbf{x}} - b(y_5 - \frac{1}{2}) \hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{21}$	$-x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 - z_5 \mathbf{a}_3$	=	$-ax_5 \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} - cz_5 \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{22}$	$(x_5 + \frac{1}{2}) \mathbf{a}_1 + y_5 \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_5 + \frac{1}{2}) \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{23}$	$x_5 \mathbf{a}_1 - (y_5 - \frac{1}{2}) \mathbf{a}_2 + z_5 \mathbf{a}_3$	=	$ax_5 \hat{\mathbf{x}} - b(y_5 - \frac{1}{2}) \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{24}$	$-(x_5 - \frac{1}{2}) \mathbf{a}_1 + (y_5 + \frac{1}{2}) \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_5 - \frac{1}{2}) \hat{\mathbf{x}} + b(y_5 + \frac{1}{2}) \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(8d)	Ag III
$\mathbf{B}_{25}$	$x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3$	=	$ax_6 \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(8d)	Te III
$\mathbf{B}_{26}$	$-(x_6 - \frac{1}{2}) \mathbf{a}_1 - y_6 \mathbf{a}_2 + (z_6 + \frac{1}{2}) \mathbf{a}_3$	=	$-a(x_6 - \frac{1}{2}) \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + c(z_6 + \frac{1}{2}) \hat{\mathbf{z}}$	(8d)	Te III
$\mathbf{B}_{27}$	$-x_6 \mathbf{a}_1 + (y_6 + \frac{1}{2}) \mathbf{a}_2 - z_6 \mathbf{a}_3$	=	$-ax_6 \hat{\mathbf{x}} + b(y_6 + \frac{1}{2}) \hat{\mathbf{y}} - cz_6 \hat{\mathbf{z}}$	(8d)	Te III
$\mathbf{B}_{28}$	$(x_6 + \frac{1}{2}) \mathbf{a}_1 - (y_6 - \frac{1}{2}) \mathbf{a}_2 - (z_6 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_6 + \frac{1}{2}) \hat{\mathbf{x}} - b(y_6 - \frac{1}{2}) \hat{\mathbf{y}} - c(z_6 - \frac{1}{2}) \hat{\mathbf{z}}$	(8d)	Te III
$\mathbf{B}_{29}$	$-x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 - z_6 \mathbf{a}_3$	=	$-ax_6 \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} - cz_6 \hat{\mathbf{z}}$	(8d)	Te III
$\mathbf{B}_{30}$	$(x_6 + \frac{1}{2}) \mathbf{a}_1 + y_6 \mathbf{a}_2 - (z_6 - \frac{1}{2}) \mathbf{a}_3$	=	$a(x_6 + \frac{1}{2}) \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} - c(z_6 - \frac{1}{2}) \hat{\mathbf{z}}$	(8d)	Te III
$\mathbf{B}_{31}$	$x_6 \mathbf{a}_1 - (y_6 - \frac{1}{2}) \mathbf{a}_2 + z_6 \mathbf{a}_3$	=	$ax_6 \hat{\mathbf{x}} - b(y_6 - \frac{1}{2}) \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}}$	(8d)	Te III

$$\mathbf{B}_{32} = -\left(x_6 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_6 + \frac{1}{2}\right) \mathbf{a}_2 + \left(z_6 + \frac{1}{2}\right) \mathbf{a}_3 = -a \left(x_6 - \frac{1}{2}\right) \hat{\mathbf{x}} + b \left(y_6 + \frac{1}{2}\right) \hat{\mathbf{y}} + c \left(z_6 + \frac{1}{2}\right) \hat{\mathbf{z}} \quad (8d) \quad \text{Te III}$$

## References

- [1] L. Bindi, P. G. Spry, and C. Cipriani, *Empressite, AgTe, from the Empress-Josephine mine, Colorado, U.S.A.: Composition, physical properties, and determination of the crystal structure*, Am. Mineral. **89**, 1043–1047 (2004).

## Found in

- [1] R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).