

# InS Structure:


## AB\_oP8\_58\_g\_g-001

This structure originally had the label **AB\_oP8\_58\_g.g.** Calls to that address will be redirected here.

Cite this page as: D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://afLOW.org/p/A7M6>

[https://afLOW.org/p/AB\\_oP8\\_58\\_g\\_g-001](https://afLOW.org/p/AB_oP8_58_g_g-001)




Prototype	InS
AFLOW prototype label	AB_oP8_58_g_g-001
ICSD	15931
Pearson symbol	oP8
Space group number	58
Space group symbol	<i>Pnmm</i>
AFLOW prototype command	<code>afLOW --proto=AB_oP8_58_g_g-001 --params=a, b/a, c/a, x1, y1, x2, y2</code>

### Simple Orthorhombic primitive vectors

$$\mathbf{a}_1 = a \hat{x}$$

$$\mathbf{a}_2 = b \hat{y}$$

$$\mathbf{a}_3 = c \hat{z}$$



### Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2$	$=$	$ax_1 \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}}$	(4g)	In I
$\mathbf{B}_2$	$= -x_1 \mathbf{a}_1 - y_1 \mathbf{a}_2$	$=$	$-ax_1 \hat{\mathbf{x}} - by_1 \hat{\mathbf{y}}$	(4g)	In I
$\mathbf{B}_3$	$= -\left(x_1 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_1 + \frac{1}{2}\right) \mathbf{a}_2 +$ $\frac{1}{2} \mathbf{a}_3$	$=$	$-a\left(x_1 - \frac{1}{2}\right) \hat{\mathbf{x}} + b\left(y_1 + \frac{1}{2}\right) \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(4g)	In I
$\mathbf{B}_4$	$= \left(x_1 + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_1 - \frac{1}{2}\right) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a\left(x_1 + \frac{1}{2}\right) \hat{\mathbf{x}} - b\left(y_1 - \frac{1}{2}\right) \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(4g)	In I
$\mathbf{B}_5$	$= x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2$	$=$	$ax_2 \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}}$	(4g)	S I
$\mathbf{B}_6$	$= -x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2$	$=$	$-ax_2 \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}}$	(4g)	S I
$\mathbf{B}_7$	$= -\left(x_2 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_2 + \frac{1}{2}\right) \mathbf{a}_2 +$ $\frac{1}{2} \mathbf{a}_3$	$=$	$-a\left(x_2 - \frac{1}{2}\right) \hat{\mathbf{x}} + b\left(y_2 + \frac{1}{2}\right) \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(4g)	S I
$\mathbf{B}_8$	$= \left(x_2 + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_2 - \frac{1}{2}\right) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$a\left(x_2 + \frac{1}{2}\right) \hat{\mathbf{x}} - b\left(y_2 - \frac{1}{2}\right) \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(4g)	S I

## References

- [1] K. Schubert, E. Dörre, and E. Günzel, *Kristallchemische Ergebnisse an Phasen aus B-Elementen*, *Naturwissenschaften* **41**, 448 (1954), doi:10.1007/BF00628872.

## Found in

- [1] P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn.